



253 Gold

DS-296F-0524

**Globally Proven
Construction Solutions**



1. NOM DU PRODUIT

253 Gold

2. FABRICANT

LATICRETE International, Inc.

1 LATICRETE Park North

Bethany, CT 06524-3423 États-Unis

Téléphone: +1.203.393.0010, poste 1235

Numéro sans frais: 1.800.243.4788, poste 1235

Télécopieur: +1.203.393.1684

Site Web: laticrete.com

3. DESCRIPTION DU PRODUIT

253 Gold is a superior polymer fortified bagged cementitious thin-set powder to be mixed with water to install ceramic tile and natural stone using the thin-set method of installation.

Utilisation

- Designed for interior and exterior floor and wall installations of all types of ceramic tiles, porcelain tile and stone over concrete, exterior glue plywood and a variety of substrates.

Avantages

- Interior and exterior.
- Exceeds ANSI A118.4, A118.11 and ISO 13007-1 (C2)
- Bonds to most surfaces.

Supports Appropriés

Conditionnement

- Blanc
 - Sac de 22,7 kg (50 lb)
- Gris
 - Sac de 11,3 kg (25 lb)
 - Sac de 22,7 kg (50 lb)
- Blanc
 - Sac de 22,7 kg (50 lb)
- Gris
 - Sac de 11,3 kg (25 lb)
 - Sac de 22,7 kg (50 lb)
- Blanc
 - Sac de 22,7 kg (50 lb)
- Gris
 - Sac de 11,3 kg (25 lb)
 - Sac de 22,7 kg (50 lb)
- Blanc
 - Sac de 22,7 kg (50 lb)
- Gris
 - Sac de 11,3 kg (25 lb)
 - Sac de 22,7 kg (50 lb)
- Blanc
 - Sac de 22,7 kg (50 lb)
- Gris
 - Sac de 11,3 kg (25 lb)
 - Sac de 22,7 kg (50 lb)

Couverture approximative

Approximately 80–95 ft² / 50 lb bag (7.4–8.8 m²/ 22.7 kg bag) with 1/4" x 1/4" (6 mm x 6 mm) notched trowel.

Approximately 60–70 ft² / 50 lb bag (5.6–6.5 m²/ 22.7 kg bag) with 1/4" x 3/8" (6 mm x 9 mm) notched trowel.

Coverage will vary depending on trowel notch size, type and size of tile and substrate.

For installing STRATA_MAT, approximately 110-120ft² /50 lb bag (10.2 – 11.1 m²/22.7 kg bag) with 1/4" x 3/16" (6mm x 5mm) notched trowel

Restrictions

- For veneer installations using this product, consult local building code requirements regarding limitations and installation system specifications.
- Not for use directly over particle board, luan, Masonite® or hardwood floors.

- Use LATAPOXY® 300 Adhesive for installing green marble, water sensitive stone, resin backed stone, or tile and agglomerates.
- Use white mortar for white or light-colored marble/stone.
- Not for use in submerged applications. For these applications, use 254 Platinum.
- Adhesives/mastics, mortars and grouts for ceramic tile, pavers, brick and stone are not designed as replacements for waterproof membranes. When a waterproof barrier is required, use a LATICRETE® Waterproofing Membrane (see Section 10 FILING SYSTEMS).
- Note: Surfaces must be structurally sound, stable and rigid enough to support ceramic/stone tile, thin brick and similar finishes. Substrate deflection under all live, dead and impact loads, including concentrated loads, must not exceed L/360 for thin bed ceramic tile/brick installations or L/480 for thin bed stone installations where L=span length (except where local building codes specify more stringent deflection requirements)

Mises en garde

- Consult SDS for more safety information.
- Some marbles and other natural stone have low flexural strength and may not be suitable for installation over wood floors.
- During cold weather, protect finished work from traffic until fully cured.
- Contains portland cement and silica sand. Causes severe skin burns and eye damage. Wear protective gloves, protective clothing and eye protection. In case of contact, flush thoroughly with water.
- Do not take internally. Silica sand may cause cancer, respiratory irritation or serious lung problems. Do not breathe dust. Wear a respirator in dusty areas.
- Keep out of reach of children.

4. DONNÉES TECHNIQUES

Informations COV/LEED sur le produit

This product has been certified for Low Chemical Emissions (ULCOM/GG UL2818) under the UL GREENGUARD Certification Program For Chemical Emissions For Building Materials, Finishes and Furnishings (UL 2818 Standard) by UL Environment.

Total VOC Content grams/liter of product in unused form is 0.00 g/L.

Propriétés physiques

Test	Test Method	Results	ANSI Specification
Porcelain Tile Shear Strength	ANSI A118.4 F-5.2.4	350–450 psi (2.4–3.1 MPa)	>200 psi (1.4 MPa)
Porcelain Tile Shear Strength Water Immersion	ANSI A118.4 F-5.2.3	200–250 psi (1.4–1.7 MPa)	>150 psi (1.03 MPa)
Quarry Tile to Plywood Shear Strength	ANSI A118.11 P-4.1.2	190–240 psi (1.3–1.6 MPa)	>150 psi (1.03 MPa)

Propriétés d'utilisation

Open Time	60 minutes
Pot Life	4 hours
Time to Heavy Traffic	24 hours
Wet Density	12.6 lb/gal (1.5 g/ml)

Caractéristiques sous réserve de modification sans préavis. Les résultats présentés sont typiques, mais ils reflètent les procédures d'essai utilisées. Les performances réelles sur le terrain dépendent des méthodes de pose et des conditions locales.

5. POSE

- All surfaces should be between 40°F (4°C) and 90°F (32°C) and structurally sound, clean and free of all dirt, oil, grease, paint, concrete sealers or curing compounds. Rough or uneven concrete surfaces should be made smooth with Latex Portland Cement Underlayment to provide a wood float (or better) finish. Dry, dusty concrete slabs or masonry should be dampened and excess water swept off. Installation may be made on a damp surface. New concrete slabs shall be damp cured and 28 days old before application. All slabs must be plumb and true to within 1/4" (6 mm) in 10 ft (3 m). Expansion joints shall be provided through the tile work from all construction or expansion joints in the substrate. Follow ANSI specification A108.01-3.7 "Requirements for Movement Joints: Preparations by Other Trades" or Tile Council of North America (TCNA) detail EJ-171 "Movement Joints—Vertical & Horizontal". Do not cover expansion joints with mortar.

1. Installer must verify that deflection under all live, dead and impact loads of interior plywood floors does not

exceed industry standards of L/360 for ceramic tile and brick or L/480 for stone installations where L=span length.

2. Minimum construction for interior plywood floors.

SUBFLOOR: 5/8" (15 mm) thick exterior glue plywood, either plain with all sheet edges blocked or tongue and groove, over bridged joints spaced 16" (400 mm) o.c. maximum; fasten plywood 6" (150 mm) o.c. along sheet ends and 8" (200 mm) o.c. along intermediate supports with 8d ring-shank, coated or hot dip galvanized nails (or screws); allow 1/8" (3 mm) between sheet ends and 1/4" (6 mm) between sheets edges; all sheet ends must be supported by a framing member; glue sheets to joints with construction adhesive.

UNDERLAYMENT: 5/8" (15 mm) thick exterior glue plywood fastened 6" (150 mm) o.c. along sheet ends and 8" (200 mm) o.c. in the panel field (both directions) with 8d ring-shank, coated or hot dip galvanized nails (or screws); allow 1/8" (3 mm) to 1/4" (6 mm) between sheets and 1/4" (6 mm) between sheet edges and any abutting surfaces; offset underlayment joints from joints in subfloor and stagger joints between sheet ends; glue underlayment to subfloor with construction adhesive. Refer to Technical Data Sheet 152 "Requirements for Direct Bonding of Ceramic or Stone Tiles Over Wood Floors" for complete details.

Mixing

Place clean, potable water into a clean pail. Use approximately 5.5 qts (5.2 L) of water for 50 lbs (22.7 kg) of powder. (To mix smaller quantities use 3.4 parts powder to 1 part water.) Add 253 Gold. Mix by hand or with a slow speed mixer to a smooth, trowelable consistency. Allow mortar to slake for 5 – 10 minutes. Remix without adding any more water or powder. During use, stir occasionally to keep mix fluffy. Do not temper with water.

Mixing with PERMACOLOR® Select Color Kits (253 Gold White only)

Requires 2 LATICRETE PERMACOLOR Select Color Kits. Each Color Kit contains 2 individual color packets, use all 4 packets) Place water in a clean mixing container. Remove color packets from the cardboard container as well as the protective plastic sleeve. The internal bag is a water dispersible packet – when using the 50 lbs. (22.7 kg) bag of 253 Gold, drop all color packets directly in to water in clean mixing container. Mix with a drill mixer until pigment is dispersed evenly in container and the dispersible packet is no longer visible. Add 253 Gold and mix as directed above. Please note that additional water may be necessary when

using PERMACOLOR Select color Kits.

Application

Apply mortar to the substrate with the flat side of the trowel, pressing firmly to work into surface. Comb on additional mortar with the notched side.

Note: Use the proper sized notched trowel to ensure full bedding of the tile. Spread as much mortar as can be covered with tile in 15–20 minutes. Back butter large tiles >8" x 8" (>200 mm x 200 mm) to provide full bedding and firm support. Place tiles into wet, sticky mortar and beat in using a beating block and rubber mallet to embed tile and adjust level. Check mortar for complete coverage by periodically removing a tile and inspecting bedding mortar transfer onto back of tile. If mortar is skinned over (not sticky), remove and replace with fresh mortar.

Grouting

Grout installation after a minimum of 24 hours curing time at 70°F (21°C). Grout with SPECTRALOCK® PRO Premium Grout†, SPECTRALOCK PRO Grout†, PERMACOLOR Select, or PERMACOLOR Grout^.

Cleaning

Clean tools and tile work with water while mortar is fresh.

6. DISPONIBILITÉ ET COÛT

Disponibilité

Les produits LATICRETE® et LATAPOXY® sont proposés dans le monde entier.

Appeler un des numéros suivants pour obtenir des informations relatives aux distributeurs:

Numéro sans frais: 1.800.243.4788

Téléphone: +1.203.393.0010

Pour obtenir de l'information en ligne de distributeurs, visiter LATICRETE à l'adresse suivante laticrete.com

Coût

Communiquez avec le distributeur LATICRETE le plus proche.

7. GARANTIE

Voir 10. SYSTÈME DE CLASSIFICATION:

- 10 Year System Warranty (US) (English)
- 1 Year Product Warranty (US) (English)

8. ENTRETIEN

LATICRETE and LATAPOXY grouts require routine cleaning with a neutral pH soap and water. All other LATICRETE and LATAPOXY materials require no maintenance but installation performance and durability may depend on properly maintaining products supplied by other manufacturers. All stone and tile should be

maintained and sealed with LATICRETE STONETECH® professional products as appropriate for the specific tile/stone and installation situation.

9. SERVICES TECHNIQUES

Soutien technique

Pour tout renseignement, appeler la ligne d'aide du service technique de LATICRETE:

Numéro sans frais: 1.800.243.4788, ext. 1235
Téléphone: +1.203.393.0010, ext. 1235
Télécopieur: +1.203.393.1948

Documentation technique et de sécurité

Pour obtenir la documentation technique et les consignes de sécurité, visiter notre site Web à laticrete.com.

10. SYSTÈME DE CLASSIFICATION

Des informations supplémentaires sur les produits sont disponibles sur notre site Web à laticrete.com. Liste des documents connexes:

- DS 230.13: LATICRETE Product Warranty
- DS 230.10: LATICRETE 10 Year System Warranty (United States and Canada)
- DS 236.0: 9235 Waterproofing Membrane
- DS 250.0: PERMACOLOR Grout[^]
- DS 281.0: PERMACOLOR Select
- DS 260.0: STRATA_MAT™
- DS 633.0: LATAPOXY 300 Adhesive
- DS 663.0: HYDRO BAN®
- DS 677.0: 254 Platinum
- DS 681.0: SPECTRALOCK PRO Premium Grout†
- DS 685.0: SPECTRALOCK PRO Grout†
- TDS 152: "Bonding Ceramic Tile, Stone or Brick Over Wood Floors"
- DS 026.0: STRATA_MAT™

LATICRETE International, Inc.

One LATICRETE Park North, Bethany, CT 06524-3423 USA • 1.800.243.4788 • +1.203.393.0010 • www.laticrete.com

© 2024 LATICRETE International, Inc. All trademarks shown are the intellectual properties of their respective owners.