



LHT™

DS-180F-0624

**Globally Proven
Construction Solutions**



1. NOM DU PRODUIT

LHT™

2. FABRICANT

LATICRETE International, Inc.

1 LATICRETE Park North

Bethany, CT 06524-3423 États-Unis

Téléphone: +1.203.393.0010, poste 1235

Numéro sans frais: 1.800.243.4788, poste 1235

Télécopieur: +1.203.393.1684

Site Web: laticrete.com

3. DESCRIPTION DU PRODUIT

A polymer modified large and heavy tile mortar specifically formulated to provide a one-step installation for large format ceramic tile, porcelain tile, marble and stone on floors.

Utilisation

- Large and Heavy Tile Mortar used as a bonding mortar from a minimum of 3/32" (2.4mm) up to a 3/4" (19mm) thickness

Avantages

- Exceeds ANSI A118.4 H
- Supports heavy tile and stone, reducing lippage problems.
- For interior and exterior floor applications
- Build up to 3/4" (19 mm) without shrinkage or set-up time problems

Supports Appropriés

Conditionnement

Sac de 22,7 kg (50 lb)

Couverture approximative

Trowel Size	ft ²	m ²
1/2" x 1/2" (12 mm x 12 mm) notched trowel	4 0 - 47	3.7 – 4.4

Restrictions

- Do not install tile/stone when surface temperatures are below freezing (32°F [0°C]).
- Adhesives/mastics, mortars and grouts for ceramic tile, pavers brick and stone are not designed as replacements for waterproofing membrane; use a LATICRETE® Waterproofing Membrane (see Section 10 FILING SYSTEMS).
- DO NOT bond to particle board, luan, Masonite® or hardwood surfaces.
- Not a remedy to level or flatten substrates. Use a suitable LATICRETE Underlayment for this purpose.
- Note: Surfaces must be structurally sound, stable and rigid enough to support ceramic/stone tile, thin brick and similar finishes. Substrate deflection under all live, dead and impact loads, including concentrated loads, must not exceed L/360 for thin bed ceramic tile/brick installations or L/480 for thin bed stone installations where L=span length.

Mises en garde

- Consult SDS for more safety information.
- Contains portland cement and silica sand. Causes severe skin burns and serious eye damage. Wear protective gloves and eye protection. In case of contact, flush thoroughly with water.
- Do not take internally. Silica sand may cause cancer, respiratory irritation or serious lung problems. Do not breathe dust. Wear a respirator in dusty areas.
- Use LATAPOXY® 300 Adhesive for installing green marble, resin backed tile or stone or water sensitive natural stone and agglomerates.
- For light-colored marble and stone use LHT white.
- Keep out of reach of children.

4. DONNÉES TECHNIQUES

Informations COV/LEED sur le produit

Total VOC Content pounds/gallon (grams/liter) of product in unused form is 0.00 g/L

Propriétés physiques

LHT™ mixed with water

Test	Test Method	Specification	Results
Porcelain Tile Shear Strength 28 day	ANSI A118.4-7.2.5	>200 psi (1.4 MPa)	300-400 psi (2.1-2.8 MPa)
Glazed Wall Tile Shear Strength 7 day	ANSI 118.4-7.1.2	>300 psi (2.1 MPa)	300-400 psi (2.1-2.8 MPa)

LHT mixed with 333 Flexible Additive

Test	Test Method	Specification	Results
Shear Bond, Quarry Tile/Plywood, 28 day	ANSI A118.11 4.1.1.2	>150 psi (1.0 MPa)	200 – 300 psi (1.4 – 2.1 MPa)

Propriétés d'utilisation

LHT mixed with water or 3701 Mortar Admix

Open Time	20 minutes
Pot Life	3–4 hours
Time to Heavy Traffic	Minimum 24 hours @ 70°F (24°C)
Wet Density	100 lbs/ft ³ (1600 kg/m ³)

Specifications subject to change without notification. Results shown are typical but reflect test procedures used. Actual field performance will depend on installation methods and site conditions.

Caractéristiques sous réserve de modification sans préavis. Les résultats présentés sont typiques, mais ils reflètent les procédures d'essai utilisées. Les performances réelles sur le terrain dépendent des méthodes de pose et des conditions locales.

5. POSE

• Surface Preparation

All surfaces should be between 40°F (4°C) and 90°F (32°C) and structurally sound, clean and free of all dirt, oil, grease, paint, concrete sealers or curing compounds. Rough or uneven concrete surfaces should be made smooth with Latex Portland Cement Underlayment to provide a wood float (or better) finish. Dry, dusty concrete slabs or masonry should be dampened and excess water swept off. Installation may be made on a damp surface. New concrete slabs shall be damp cured and 28 days old before application. There is no minimum cure time for concrete slabs when mortar is mixed with latex additive. All slabs must be plumb and true to within

1/4" (6 mm) in 10 ft (3 m). Expansion joints shall be provided through the tile work from all construction or expansion joints in the substrate. Follow ANSI specification A108.01-3.7 "Requirements for Movement Joints: Preparations by Other Trades" or TCNA detail EJ-171 "Movement Joints—Vertical & Horizontal". Do not cover expansion joints with mortar.

1. Installer must verify that deflection under all live, dead and impact loads of interior plywood floors does not exceed industry standards of L/360 for ceramic tile and brick or L/480 for stone installations where L=span length.
2. Minimum construction for interior plywood floors.

SUBFLOOR: 5/8" (16 mm) thick exterior glue plywood, either plain with all sheet edges blocked or tongue and groove, over bridged joints spaced 16" (400 mm) o.c. maximum; fasten plywood 6" (150 mm) o.c. along sheet ends and 8" (200 mm) o.c. along intermediate supports with 8d ring-shank, coated or hot dip galvanized nails (or screws); allow 1/8" (3 mm) between sheet ends and 1/4" (6 mm) between sheets edges; all sheet ends must be supported by a framing member; glue sheets to joints with construction adhesive.

UNDERLAYMENT: 5/8" (16 mm) thick exterior glue plywood fastened 6" (150 mm) o.c. along sheet ends and 8" (200 mm) o.c. in the panel field (both directions) with 8d ring-shank, coated or hot dip galvanized nails (or screws); allow 1/8" (3 mm) to 1/4" (6 mm) between sheets and 1/4" (6 mm) between sheet edges and any abutting surfaces; offset underlayment joints from joints in subfloor and stagger joints between sheet ends; glue underlayment to subfloor with construction adhesive. Refer to Technical Data Sheet 152 Bonding Ceramic Tile, Stone or Brick Over Wood Floors for complete details.

Mixing

Mix one 50 lb (22.7 kg) bag of LHT™ as follows: 4.6 to 4.9 qts (4.4 to 4.6 L) of water or 3701 Mortar Admix; or 6.9 to 7.2 qts (6.5 to 6.8 L) of 333 Flexible Additive. To mix smaller quantities use 3.6 parts powder to 1 part water. Place clean, potable water or admix/additive into a clean pail. Add LHT powder. Mix by hand or with a slow speed mixer to a smooth, trowelable consistency. Allow mortar to slake 5–10 minutes. Remix and apply with the proper sized notched trowel.

Application

Apply mortar to substrate with flat side of trowel, pressing firmly to work into surface. Comb on additional mortar with the notched side, use 1/2" x 1/2" (12 mm x 12 mm) or 3/4" (18 mm) half

loop trowel. Spread as much mortar as can be covered with tile in 15–20 minutes. Back butter large > 8" x 8" (>200 mm x 200 mm) irregular backed tiles to provide full bedding and firm support. Place tiles into wet, sticky mortar and beat in using a beating block and rubber mallet to embed tile and to adjust level. Check mortar for complete coverage periodically removing a tile and inspecting bedding mortar transfer onto back of tile. If mortar is skimmed over (not sticky) remove and replace with fresh mortar.

Grouting

Grout installation after a minimum of 24 hours curing time at 70°F (21°C). Grout with SPECTRALOCK® PRO Premium Grout†, SPECTRALOCK® PRO Grout†, PERMACOLOR® SELECT, PERMACOLOR Select NS or PERMACOLOR Grout?.

Cold Weather Note: The setting of portland cement mortars and grouts are retarded by low temperatures. Protect finished work for an extended period when installing in cold weather. Do not set tile when surface temperature is below freezing or when substrate is frozen.

Hot Weather Note: The evaporation of moisture in portland cement mortars is accelerated by hot, dry conditions. Apply to dampened surfaces and protect freshly spread mortar and finished work when installing in hot temperatures.

Cleaning

Clean tools and tile work with water while mortar is fresh.

6. DISPONIBILITÉ ET COÛT

Disponibilité

Les produits LATICRETE® et LATAPOXY® sont proposés dans le monde entier.

Appeler un des numéros suivants pour obtenir des informations relatives aux distributeurs:

Numéro sans frais: 1.800.243.4788

Téléphone: +1.203.393.0010

Pour obtenir de l'information en ligne de distributeurs, visiter LATICRETE à l'adresse suivante laticrete.com

Coût

Communiquez avec le distributeur LATICRETE le plus proche.

7. GARANTIE

Voir 10. SYSTÈME DE CLASSIFICATION:

- 5 Year System Warranty (US) (English)
- 1 Year Product Warranty (US) (English)

8. ENTRETIEN

LATICRETE and LATAPOXY grouts require routine cleaning with a neutral pH soap and water. All other LATICRETE and LATAPOXY materials require no maintenance but installation performance and durability may depend on properly maintaining products supplied by other manufacturers.

9. SERVICES TECHNIQUES

Soutien technique

Pour tout renseignement, appeler la ligne d'aide du service technique de LATICRETE:

Numéro sans frais: 1.800.243.4788, ext. 1235

Téléphone: +1.203.393.0010, ext. 1235

Télécopieur: +1.203.393.1948

Documentation technique et de sécurité

Pour obtenir la documentation technique et les consignes de sécurité, visiter notre site Web à laticrete.com.

10. SYSTÈME DE CLASSIFICATION

Des informations supplémentaires sur les produits sont disponibles sur notre site Web à laticrete.com. Liste des documents connexes:

- DS 230.13: LATICRETE Product Warranty
- DS 230.05: LATICRETE 5 Year System Warranty
- DS 236.0: 9235 Waterproofing Membrane
- DS 250.0: PERMACOLOR® Grout?
- DS 281.0: PERMACOLOR Select
- DS 633.0: LATAPOXY 300 Adhesive
- DS 663.0: HYDRO BAN®
- DS 681.0: SPECTRALOCK® PRO Premium Grout†
- DS 685.0: SPECTRALOCK PRO Grout†
- TDS 152: Bonding Ceramic Tile, Stone or Brick Over Wood Floors
- DS 116.0: PERMACOLOR Select NS

LATICRETE International, Inc.

One LATICRETE Park North, Bethany, CT 06524-3423 USA • 1.800.243.4788 • +1.203.393.0010 • www.laticrete.com

© 2024 LATICRETE International, Inc. All trademarks shown are the intellectual properties of their respective owners.