



254R Platinum Rápido Adhesivo Multiuso

DS-729E-0524

**Globally Proven
Construction Solutions**



1. NOMBRE DEL PRODUCTO

254R Platinum Rápido Adhesivo Multiuso

2. FABRICANTE

LATICRETE International, Inc.
1 LATICRETE Park North
Bethany, CT 06524-3423 USA

Teléfono: +1.203.393.0010, ext. 1235

Línea telefónica gratuita: 1.800.243.4788, ext.

1235

Fax: +1.203.393.1684

Sitio de Internet: laticrete.com

3. DESCRIPCIÓN DEL PRODUCTO

The ultimate one-step, polymer fortified, thin-set mortar for interior and exterior installation of ceramic tile, stone, quarry tile, pavers and brick. 254R Platinum Rapid is designed to mix with water and provide unsurpassed adhesion and workability.

Equipped with Microban Anti-Microbial Protection

Usos

- Excellent for exterior and under water applications, with a superior bond to exterior glue plywood and concrete. 254R Platinum Rapid is the ultimate rapid setting adhesive for porcelain tiles.

Ventajas

- Contains antimicrobial protection to inhibit the growth of stain-causing mold and mildew in the substrate.
- Exceeds ANSI A118.4 Requirements & ANSI A118.11.

- Rapid Set Mortar; can be grouted in 2–4 hours.
- Ultimate adhesion for porcelain tiles.
- Incredible bond to exterior glue plywood and concrete*.
- Excellent shear bond strength.
- Superior adhesion for submerged applications.
- High performing smooth creamy formula.
- * See limitations.

Sustratos adecuados

Presentación

Bolsa de 11.3 kg (25 lb)

Rendimiento aproximado

40–47 ft ² / 25 lb bag (3.7–4.4 m ² /11.3 kg bag) with 1/4" x 1/4" (6 mm x 6 mm) notched trowel.
25–30 ft ² / 25 lb bag (2.3–2.8 m ² /11.3 kg bag) with 1/4" x 3/8" (6 mm x 9 mm) notched trowel.
20–23 ft ² / 25 lb bag (1.9–2.1 m ² /11.3 kg bag) with 1/2" x 1/2" (12 mm x 12 mm) notched trowel.

Coverage will vary depending on trowel notch size, type and size of tile and substrate.

Limitaciones

- Not for use directly over particle board, luan, Masonite® or hardwood floors.
- For veneer installations using this product, consult local building code requirements regarding limitations and installation system specifications.
- Wait 14 days after the final grouting period before filling water features with water at 70°F (21°C).
- Use LATAPOXY® 300 Adhesive for installing green marble, resin backed, or water sensitive tile, stone and agglomerates.
- Adhesives/mastics, mortars and grouts for ceramic tile, pavers, brick and stone are not replacements for waterproofing membranes. When a waterproofing membrane is required, use a LATICRETE® Waterproofing Membrane (see Section 10 FILING SYSTEMS).
- Note: Surfaces must be structurally sound, stable and rigid enough to support ceramic/stone tile, thin brick and similar finishes. Substrate deflection under all live, dead and impact loads, including concentrated loads, must not exceed L/360 for thin bed ceramic tile/brick

installations or L/480 for thin bed stone installations where L=span length (except where local building codes specify more stringent deflection requirements)

trabajo dependerá de los métodos de instalación y de las condiciones del lugar.

Precauciones

- Consult SDS for more safety information.
- Some marbles and other stones have low flexural strength and may not be suitable for installation over wood floors.
- During cold weather, protect finished work from traffic until fully cured.
- Use white mortar for white or light-colored stone.
- Contains portland cement and silica sand. Causes severe skin burns and serious eye damage. Wear protective gloves, protective clothing, and eye protection. In case of contact, flush thoroughly with water.
- DO NOT take internally. Silica sand may cause cancer, respiratory irritation or serious lung problems. Do not breathe dust. Wear a respirator in dusty areas.
- For green, resin backed and moisture sensitive stones and agglomerates, use LATAPOXY® 300 Adhesive (refer to Data Sheet 633.0).
- Keep out of reach of children.

4. DATOS TÉCNICOS

Propiedades físicas

Test/Test Method	Results	ANSI Specs
Shear Bond, Porcelain Tile, 28 day cure ANSI A118.4-5.2.4	400–450 psi (2.8–3.1 MPa)	200 psi (1.4 MPa)
Shear Bond, Porcelain Tile Water Immersion ANSI A118.4-5.2.3	200–220 psi (1.4–1.5 MPa)	150 psi (1.0 MPa)
Shear Bond, Quarry Tile/Plywood ANSI A118.11	190–230 psi (1.3–1.6 MPa)	150 psi (1.0 MPa)

Propiedades de trabajo

Open Time	30 minutes
Pot Life	50 minutes
Time to Grout	2–4 hours
Time to Heavy Traffic	5 hours

Specifications subject to change without notification. Results shown are typical but reflect test procedures used. Actual field performance will depend on installation methods and site conditions

Las especificaciones están sujetas a cambios sin notificación. Los resultados exhibidos son representativos pero reflejan los procedimientos de prueba utilizados. El desempeño real en el área de

5. INSTALACIÓN

• Surface Preparation

All surfaces should be between 40°F (4°C) and 90°F (32°C) and structurally sound, clean and free of all dirt, oil, grease, paint, concrete sealers or curing compounds. Rough or uneven concrete surfaces should be made smooth with LATICRETE Latex Portland Cement Underlayment to provide a wood float (or better) finish. Dry, dusty concrete slabs or masonry should be dampened and excess water swept off. Installation may be made on a damp surface. New concrete slabs must be damp cured and at least 28 days old prior to application. Expansion joints shall be provided through the tile work from all construction or expansion joints in the substrate. Follow ANSI specification A108.01-3.7 “Requirements for Movement Joints: Preparations by Other Trades” or TCNA detail EJ-171 “Movement Joints–Vertical & Horizontal”. Do not cover expansion joints with mortar.

1. Installer must verify that deflection under all live, dead and impact loads of interior plywood floors does not exceed industry standards of L/360 for ceramic tile and brick or L/480 for stone installations where L=span length.
2. Minimum construction for interior plywood floors.

SUBFLOOR: 5/8" (15 mm) thick exterior glue plywood, either plain with all sheet edges blocked or tongue and groove, over bridged joints spaced 16" (400 mm) o.c. maximum; fasten plywood 6" (150 mm) o.c. along sheet ends and 8" (200 mm) o.c. along intermediate supports with 8d ring-shank, coated or hot dip galvanized nails (or screws); allow 1/8" (3 mm) between sheet ends and 1/4" (6 mm) between sheets edges; all sheet ends must be supported by a framing member; glue sheets to joints with construction adhesive.

UNDERLAYMENT: 5/8" (15 mm) thick exterior glue plywood fastened 6" (150 mm) o.c. along sheet ends and 8" (200 mm) o.c. in the panel field (both directions) with 8d ring-shank, coated or hot dip galvanized nails (or screws); allow 1/8" (3 mm) to 1/4" (6 mm) between sheets and 1/4" (6 mm) between sheet edges and any abutting surfaces; offset underlayment joints from joints in subfloor and stagger joints between sheet ends; glue underlayment to subfloor with construction adhesive. Refer to Technical Data Sheet 152 “Bonding Ceramic Tile, Stone or Brick Over Wood Floors” for complete details.

Mixing

Place clean, potable water into a clean pail. Add 254R Platinum Rapid. Use approximately 2.9 - 3 qts (2.7 - 2.9 L) of water for 25 lbs (11.3 kg) of powder. (To mix smaller quantities use 3.1 parts powder to 1 part water.) Mix by hand or with a slow speed mixer to a smooth, trowelable consistency. Remix without adding any more water or powder. During use, stir occasionally to keep mix fluffy. **Do not** temper with water.

Application

Apply mortar to the substrate with the flat side of the trowel, pressing firmly to work into surface. Comb on additional mortar with the notched side.

Note: Use proper sized notched trowel to ensure full bedding of the tile. Spread as much mortar as can be covered with tile in 15–20 minutes. Back butter large tiles >8" x 8" (>200 mm x 200 mm) to provide full bedding and firm support. Place tiles into wet, sticky mortar and beat in using a beating block and rubber mallet to embed tile and adjust level. Check mortar for complete coverage by periodically removing a tile and inspecting bedding mortar transfer onto back of tile. If mortar is skinned over (not sticky), remove and replace with fresh mortar.

Grouting

Grout installation after a minimum of 2-4 hours curing time at 70°F (21°C). Grout with SPECTRALOCK® PRO Premium Grout†, SPECTRALOCK PRO Grout†, PERMACOLOR® Select, PERMACOLOR®^ Grout, or 1500 Sanded Grout or 1600 Unsanded Grout gauged with 1776 Grout Enhancer.

Cleaning

Clean tools and tile work with water while mortar is fresh.

6. DISPONIBILIDAD Y COSTO

Disponibilidad

Los materiales LATICRETE® y LATAPOXY® están disponibles en todo el mundo.

Para obtener información sobre los distribuidores, llame a:

Línea telefónica gratuita: 1.800.243.4788

Teléfono: +1.203.393.0010

Para obtener información sobre los distribuidores en Internet, visite LATICRETE en laticrete.com

Costo

Comuníquese con un distribuidor de LATICRETE de su zona.

7. GARANTÍA

Consulte la Sección 10. SISTEMAS ESPECIALES:

- 25 Year System Warranty (US) (English)
- 1 Year Product Warranty (US) (English)
- LATICRETE Lifetime System Warranty (US) (English)

8. MANTENIMIENTO

LATICRETE and LATAPOXY grouts require routine cleaning with a neutral pH soap and water. All other LATICRETE and LATAPOXY materials require no maintenance but installation performance and durability may depend on properly maintaining products supplied by other manufacturers. All stone and tile should be maintained and sealed with LATICRETE STONETECH® professional products as appropriate for the specific tile/stone and installation situation.

9. DEPARTAMENTO DE ASISTENCIA TÉCNICA

Asistencia técnica

Para obtener más información, comuníquese con la Línea Directa del Departamento de Asistencia Técnica de LATICRETE:

Línea telefónica gratuita:

1.800.243.4788, ext. 1235

Teléfono: +1.203.393.0010, ext. 1235

Fax: +1.203.393.1948

Material informativo sobre aspectos técnicos y de seguridad

Para obtener material sobre aspectos técnicos y de seguridad, visite nuestro sitio web en laticrete.com.

10. SISTEMAS ESPECIALES

Podrá obtener más información sobre los productos en nuestro sitio web laticrete.com. A continuación, encontrará una lista de documentos afines:

- DS 230.13: LATICRETE Product Warranty
- DS 025.0: LATICRETE 25 Year System Warranty (United States and Canada)
- DS 230.99: LATICRETE Lifetime System Warranty (United States and Canada)
- DS 236.0: 9235 Waterproofing Membrane

LATICRETE International, Inc.

One LATICRETE Park North, Bethany, CT 06524-3423 USA • 1.800.243.4788 • +1.203.393.0010 • www.laticrete.com

© 2024 LATICRETE International, Inc. All trademarks shown are the intellectual properties of their respective owners.

- DS 250.0: PERMACOLOR? Grout
- DS 281.0: PERMACOLOR Select
- DS 256.0: 1500 Sanded Grout
- DS 258.0: 1600 Unsanded Grout
- DS 264.0: 1776 Grout Enhancer
- DS 633.0: LATAPOXY 300 Adhesive
- DS 681.0: SPECTRALOCK PRO Premium Grout
- DS 685.0: SPECTRALOCK PRO Grout
- TDS 152: “Bonding Ceramic Tile, Stone or Brick Over Wood Floors”