



# PERMACOLOR® Select NS Grout Base

DS-116-0326

**Globally Proven  
Construction Solutions**



## 1. PRODUCT NAME

PERMACOLOR® Select NS Grout Base

## 2. MANUFACTURER

LATICRETE International, Inc.  
1 LATICRETE Park North  
Bethany, CT 06524-3423 USA

Telephone: +1.203.393.0010, ext. 1235

Toll Free: 1.800.243.4788, ext. 1235

Fax: +1.203.393.1684

Website: [laticrete.com](http://laticrete.com)

## 3. PRODUCT DESCRIPTION

An ultra premium, factory prepared, polymer fortified unsanded portland cement base grout designed for highly-delicate surfaces, such as high polish marble and soft glass. PERMACOLOR Select NS Grout Base should be mixed with water and LATICRETE COLOR KITS – the industry's first dispersible dry pigment solution. The only unsanded grout that exceeds ANSI 118.7. Formulated from a blend of high strength portland cement, polymers. Provides a grout joint that is dense, hard and durable in a multitude of colors.

Equipped with antimicrobial product protection.

### Uses

- For joints up to 1/2" (12 mm) between soft bisque glazed wall tile, non-vitreous clay tile, marble, stone and porcelain or glass.

### Advantages

- Mix with water and desired PERMACOLOR Select Color Kit
- Equipped with STONETECH Sealer Technology
- Contains antimicrobial technology to protect the treated article
- Excellent for wet and dry areas
- Non-shrinking
- Easy maintenance
- Easy application and clean-up
- Available in 80 stocked colors including 40 LATICRETE colors, the top 10 colors from 4 competitor's and thousands of possible colors from the Sherwin-Williams®\* and Benjamin Moore®\* palettes in the PERMACOLOR Select ANYCOLOR™ Program.
- No pre-soaking or wetting tile
- No damp curing required
- For interior, exterior and submerged use\* Sherwin-Williams and Benjamin Moore have no involvement with this program.

### Suitable Substrates

### Packaging

8 lb (3.6 kg) carton; 4 cartons per carton; 44 cartons per pallet

### Limitations

- Do not use where chemical resistance is required. Instead, use SPECTRALOCK® 2000 IG.
- Do not use acid to clean colored grout joints.
- Do not allow grout to harden on the face of the tile; clean promptly.
- Jobsite conditions can affect the final color of colored grouts. Try a small test area to determine your results before grouting entire installation.
- Certain types of tile are more absorbent than others and may stain during grouting. Prior to grouting, test a tile with the grout selected.
- Use a grout release or sealer if required.
- PERMACOLOR Select NS Grout Base is designed to be mixed with water and (1) PERMACOLOR Select Color Kit packet of desired color. Do not mix other grout additives with this product. Use of other grout

additives may result in color variation and reduced product performance and will void all LATICRETE warranties.

- Adhesives/mastics, mortars and grouts for ceramic tile, pavers, brick and stone are not replacements for waterproofing membranes. When a waterproofing membrane is required, use a LATICRETE Waterproofing Membrane (see Section 10 FILING SYSTEMS).
- Note: Surfaces must be structurally sound, stable and rigid enough to support ceramic/stone tile, thin brick and similar finishes. Substrate deflection under all live, dead and impact loads, including concentrated loads, must not exceed L/360 for thin bed ceramic tile/brick installations or L/480 for thin bed stone installations where L=span length.

### Cautions

- Consult SDS for more safety information.
- During cold weather, protect finished work from traffic until fully cured.
- Contains portland cement. Causes severe skin burns and eye damage. Wear protective gloves, clothing and eye protection. In case of contact, flush thoroughly with water.
- In submerged applications or steam rooms, allow PERMACOLOR® Select NS Grout Base to cure for 14 days at 70°F (21°C) before use of area and filing with water. See TDS 192 for more information on these applications.
- DO NOT take internally.
- Do not breathe dust. Wear a respirator in dusty areas.
- Keep out of reach of children

## 4. TECHNICAL DATA

### VOC/LEED Product Information

Total VOC Content pounds/gallon (grams/liter) of product in unused form is 0.00 lb/gal (0.00 g/ ).

### Applicable Standard

- ANSI A118.7

This product currently has a Product Specific (Type III) Environmental Product Declaration (EPD). The PCR review, life cycle assessment and declaration were independently verified by UL Environment in accordance with ISO 14025, ISO 14040 and ISO 14044.

### Physical Properties

PERMACOLOR Select NS Grout Base mixed with Water (70°F [21°C])

Test	Method	Results	Specification
Flexural Strength	ANSI A118.7 H- 3.7	1000–1400 psi (6.9-9.7 MPa)	> 1000 psi (6.9 MPa)
Linear Shrinkage 27 days	ANSI A118.7 H- 3.3	0.1–0.14 %	< 0.3 %
Tensile Strength 28 Days	ANSI A118.7 H- 3.6	500-600 psi (3.4-4.1 MPa)	> 500 psi (3.4 MPa)
Compressive Strength 28 Days	ANSI A118.7 H- 3.5	4500-5200 psi (31.0- 35.8 MPa)	> 3000 psi (20.7 MPa)

### Working Properties

PERMACOLOR Select NS Grout Base mixed with Water (70°F [21°C])

Pot Life	50-55 min (set time 90 min)
Wet Density	12.7 lb/gal (1.52 g/cm <sup>3</sup> )

Specifications subject to change without notification. Results shown are typical but reflect test procedures used. Actual field performance will depend on installation methods and site conditions.

## 5. INSTALLATION

### Surface Preparation

Before starting to grout, remove spacers and debris in grout joints and remove dust and dirt using a wet sponge. Do not leave water standing in joints. Substrate temperature must be between 40°F (4°C) and 90°F (32°C). Refer to Grout Troubleshooting Guide for more information on grouting.

### Mixing

Use approximately .9-1 qts (1.0-1.13L) of clean potable water for 8 lbs (3.6 kg) carton. Then take (1) Pigment Packet from the PERMACOLOR Select Color Kit and place in the water and agitate until the pigment is dispersed within the water. Then add the PERMACOLOR Select NS Grout Base to the water and pigment and mix slowly either by hand or with a slow speed mixer to a smooth, stiff consistency. Allow to slake for 5– 10 minutes and remix for 1 minute.

### Application

Dampen tile surface with water. Spread with a sharp, firm rubber grout float. Work the grout paste into the joints until completely filled. Use diagonal strokes to pack the joints. Ensure that joint is filled and grout is not just sitting on top (i.e. “bridging the joint”).

### Cleaning

- For first cleaning wait approximately 35 – 40 minutes at 70°F (21°C). Wider joints or cooler temperatures may extend wait time. Begin initial cleaning by lightly wiping down entire area to be cleaned with a damp

sponge. Wash with a damp sponge (not wet). Work diagonally to the joints. Allow to dry 3 hours at 70°F (21°C).

- For second cleaning use a damp sponge or dry cloth to remove remaining grout haze.
- *Note: Use caution when grouting soft glazed tile or polished stone.*

*If grout is to be sealed, LATICRETE generally recommends waiting a minimum of a 72 hours at 70°F (21°C) prior to sealing PERMACOLOR Select, with a STONETECH® sealer.*

## Selecting Other Grout Materials

LATICRETE has grouting materials designed for every use. For maximum stain resistance in most installations choose SPECTRALOCK® PRO Premium Grout For installations that require high strength and chemical resistance choose SPECTRALOCK 2000 IG. These products are ideal for installations where a stain resistant, colorfast grout is desired.

## 6. AVAILABILITY AND COST

### Availability

LATICRETE materials are available worldwide.

### For Distributor Information, Call:

Toll Free: 1.800.243.4788

Telephone: +1.203.393.0010

For on-line distributor information, visit LATICRETE at [laticrete.com](http://laticrete.com)

### Cost

Contact a LATICRETE Distributor in your area.

## 7. WARRANTY

See 10. FILING SYSTEM:

- Lifetime System Warranty (US) (English)
- Lifetime System Warranty (Canada) (English)

## 8. MAINTENANCE

LATICRETE recommends using STONETECH® surface products to protect, clean and enhance stone, masonry, tile and grout surfaces. Protect surfaces from common stains by using a STONETECH sealer such as STONETECH BulletProof® Sealer. Routine maintenance should follow with STONETECH Revitalizer® Cleaner and Protector or a neutral pH cleaner such as STONETECH Stone & Tile Cleaners. For tough or difficult to remove soil use STONETECH KlenzAll™ Cleaner, a nylon scrubbing pad or a long handled stiff bristle brush. For additional information, please refer to the Grout Guide, TDS 400 and TDS 113 Cement Grout Care & Maintenance for more information.

## 9. TECHNICAL SERVICES

### Technical Assistance

Information is available by calling the LATICRETE Technical Service Hotline:

Toll Free: 1.800.243.4788, ext. 1235

Telephone: +1.203.393.0010, ext. 1235

Fax: +1.203.393.1948

### Technical and Safety Literature

To acquire technical and safety literature, please visit our website at [laticrete.com](http://laticrete.com).

## 10. FILING SYSTEM

Additional product information is available on our website at [laticrete.com](http://laticrete.com). The following is a list of related documents:

- DS 230.13: LATICRETE® Product Warranty
- DS 030.0: SPECTRALOCK® 2000 IG
- DS 681.0.: SPECTRALOCK PRO Premium Grout

---

LATICRETE International, Inc.

One LATICRETE Park North, Bethany, CT 06524-3423 USA • 1.800.243.4788 • +1.203.393.0010 • [www.laticrete.com](http://www.laticrete.com)

© 2026 LATICRETE International, Inc. All trademarks shown are the intellectual properties of their respective owners.