



NXT™ Capa Delgada

DS-506E-0923

**Globally Proven
Construction Solutions**



- Apply from skim depth to 1" (25 mm)
- Contains no respirable crystalline silica levels that exceed the OSHA action level*
- It can be placed on substrates measuring 100% RH
- Rated for exterior use
- Can be used under and over moisture vapor barriers
- Caster Wheel Safe
- 40% lighter weight formula
- Fantastic workability and consistent results
- High coverage rate
- Direct replacement for NXT Skim, SUPERCAP SkimCoat, DRYTEK Skimcoat
- Can be applied over Gypsum based substrates * OSHA action level set forth in OSHA's Respirable Crystalline Silica (RCS) standard for construction, 29 CFR 1926.1153, as tested by an independent laboratory to be below the OSHA action level for respirable crystalline silica - see laticrete.com/silica

1. NOMBRE DEL PRODUCTO

NXT™ Capa Delgada

2. FABRICANTE

LATICRETE International, Inc.
1 LATICRETE Park North
Bethany, CT 06524-3423 USA

Teléfono: +1.203.393.0010, ext. 1235

Línea telefónica gratuita: 1.800.243.4788, ext.

1235

Fax: +1.203.393.1684

Sitio de Internet: laticrete.com

3. DESCRIPCIÓN DEL PRODUCTO

Skim Lite is a premium quality, high yielding, fast-drying, fiber reinforced, cement-based underlayment designed for skim-coating, smoothing and leveling prior to the application of floor coverings. For interior and exterior applications. Skim Lite offers the customer light weight properties while maintaining strong surface, being rated for caster wheel use. With installer safety in mind, this product contains no respirable crystalline silica levels that exceed the OSHA action level*.

Usos

- Repairs

Ventajas

- Rapid setting formula
- Ready for finished flooring in as soon as 20 minutes
- Fiber Reinforced
- High polymer content

Sustratos adecuados

Presentación

Bolsas de papel de 4.5 kg (10 lb)

Rendimiento aproximado

Substrate	Coverage at a feather-edge/skim
Smooth Profile (Underlay., Plywood, etc.)	380 SQ FT** (35.3 M ²)
Rough Profile (Concrete, OSB, etc.)	190 SQ FT** (17.6 M ²)

**Calculated coverage indicated is approximate. Coverage will vary depending on the texture of the surface and/or the thickness the material is applied at.

Limitaciones

- Do not install LATICRETE® SKIM LITE over particleboard, chipboard, hardboard (Masonite®), Luan panels, asbestos, asphalt, coal tar, or lightweight insulating concrete or any other dimensionally unstable materials.
- Do not install when surface temperature is below 40°F (4°C) or above 90°F (32°C).
- Do not install over painted surfaces.
- Do not exceed recommended mixing ratio as indicated in mixing instructions. Over watering will weaken product properties.

- Adhesives/mastics, mortars and grouts for ceramic tile, pavers, brick and stone are not replacements for waterproofing membranes. When a waterproofing membrane is required, use a LATICRETE® Waterproofing Membrane on top of the dry SKIM LITE.
- Not for use in submerged applications.
- During cold weather, protect finished work from traffic until fully cured.
- Always refer to finished floor manufacturer's recommendations regarding installation instructions, restrictions, moisture conditions and compatibility.
- Always test performance suitability and compatibility of finished floor systems prior to their application. Sample surfaces should be installed as a field test so as to be representative of entire surface and tested for intended use.

Precauciones

- Read and understand the Product Data Sheet and Safety Data Sheet.
- Check www.laticrete.com for any technical bulletins or updated information about the product and its application.
- Contact your local LATICRETE Technical Sales Representative with any questions.
- Consult SDS for more safety information.
- Contains portland cement. Causes severe skin burns and serious eye damage. May cause an allergic skin reaction. Wear protective clothing, gloves and eye protection. In case of contact, flush thoroughly with water.
- Do not take internally.
- Keep out of reach of children.

4. DATOS TÉCNICOS

Propiedades físicas

Technical Data	Results
Set Time	15 to 20 minutes*

*Drying time is a function of jobsite temperature and other conditions such as humidity and/or installation thickness. Low substrate temperatures and/or high ambient humidity will extend the drying time.

Las especificaciones están sujetas a cambios sin notificación. Los resultados exhibidos son representativos pero reflejan los procedimientos de prueba utilizados. El desempeño real en el área de trabajo dependerá de los métodos de instalación y de las condiciones del lugar.

5. INSTALACIÓN

Preparing surface for Concrete Substrate

- Clean substrate to eliminate dust, dirt, oil, grease, paint or any contaminants which may inhibit bonding.

Do not use chemicals to clean substrate. Remove any loose particles and vacuum.

- Test surface bond strength of substrate. If minimum 100 psi (0.7 MPa) bond strength is not achieved or the substrate is contaminated, remove contaminants by mechanical means. Retest surface.
- Inspect for contraction joints, construction joints, and cracks in the substrate which may be subject to movement after installation of LATICRETE® SKIM LITE. These must be maintained as joints in the new surface.
- Maintain substrate temperature between 40°F (4°C) and 90°F (32°C) during application and air temperature between 50–90°F (10–32°C) during drying. Provide adequate ventilation to ensure uniform drying.
- For very absorptive concrete, apply a fine mist of water on top of the prepared concrete using a pump garden type sprayer, just prior to SKIM LITE application. Concrete should readily absorb water. Broom out excess standing water. Do not apply SKIM LITE where there is standing water on top of the concrete. If water beads or does not absorb within 60 seconds, additional surface prep is needed.

Preparing for poured Gypsum Underlayment

- Tensile strength of the gypsum underlayment must be at least 100 psi (0.7 MPa), tested in accordance with ASTM C1583.
- Any loose or damaged poured gypsum underlayment will have to be repaired.
- All dirt, oil, paint, laitance, efflorescence, sealers, curing compounds, dust, construction debris, and any other bond breaking contaminants must be removed by diamond grinding or shot blasting.
- Use of chemicals to remove contaminants is prohibited. Use of sweeping compound is not recommended as they may contain oil which will act as a bond breaker.

Embossing Non-Cushioned Vinyl Floors and VCT

Completely remove any wax or other coatings. Roughen smooth surfaces. Wash and rinse thoroughly with clean water. Allow to dry.

Preparing Ceramic Tile or Terrazzo

Ensure tiles are well bonded to the substrate.

Mechanically abrade with a carborundum disk. Wash and rinse thoroughly with clean water. Allow to dry.

Preparing Non-Water Soluble Cutback Adhesive

Scrape non-water soluble cutback adhesive residue from the floor and remove excess material. Ensure remaining adhesive residue is completely dry.

Mixing with water

Mix 1.75 qts. to (1.7 L) 2.0 qts. (1.9 L) of clean cool water per 8 lb. (3.6 kg) bag of LATICRETE® SKIM LITE. Add product to water and mix for 3 to 4 minutes with a heavy duty drill (650 rpm or more) to obtain a lump free mix.

(Mixing with NXT EMBOSSING ADMIX (for embossing non-cushioned vinyl and VCT flooring))

Mix 2.4 qts. (2.3 L) of NXT EMBOSSING ADMIX per 8 lb. (3.6 kg) bag of SKIM LITE. Add SKIM LITE to NXT EMBOSSING ADMIX and mix for 3 minutes with a heavy duty drill (650 rpm) to obtain a lump free mix.

Note:

- **Material can be re-mixed to extend pot-life but do NOT add more water when re-mixing.**
- **A Helix Paint Mixer is not preferred.**

Application

Apply blended material to substrate with trowel at a thickness from feather-edge to 1" (25 mm) for all surfaces. After initial set of material (approx. 10–15 min.), remove all overlap marks, seams and inconsistencies by scraping with a steel trowel. Key in but do not over trowel. Material can be walked on after 15 to 20 minutes at 70°F (21°C) or higher, depending on thickness.

Flooring Installation

Finished floor goods may be installed as soon as 20 minutes after application, subject to thickness, drying conditions and type of flooring materials. Always refer to finished floor manufacturer's recommendations regarding installation instructions, restrictions, moisture conditions and compatibility. Always test performance suitability and compatibility of finished floor systems prior to their application. Sample surfaces should be installed as a field test so as to be representative of entire surface and tested for intended use.

Note: HYDRO BAN™, HYDRO BAN™ Quick Cure, and any VAPOR BAN™ moisture vapor barrier can be installed over Skim Lite with a minimum cure of 2 hours. Skim Lite can be placed over any VAPOR BAN moisture vapor barrier.

Wear Surface

Skim Lite is not to be used as a permanent wear surface. Skim Lite must be covered by a suitable floor covering material, such as carpet, vinyl flooring, ceramic tile, etc..

6. DISPONIBILIDAD Y COSTO

Disponibilidad

Los materiales LATICRETE® y LATAPOXY® están disponibles en todo el mundo.

Para obtener información sobre los distribuidores, llame a:

Línea telefónica gratuita: 1.800.243.4788
Teléfono: +1.203.393.0010

Para obtener información sobre los distribuidores en Internet, visite LATICRETE en laticrete.com

Costo

Comuníquese con un distribuidor de LATICRETE de su zona.

7. GARANTÍA

Consulte la Sección 10. SISTEMAS ESPECIALES:

- 1 Year Product Warranty (US - English)

8. MANTENIMIENTO

Non-finish LATICRETE and LATAPOXY installation materials require no maintenance but installation performance and durability may depend on properly maintaining products supplied by other manufacturers.

9. DEPARTAMENTO DE ASISTENCIA TÉCNICA

Asistencia técnica

Para obtener más información, comuníquese con la Línea Directa del Departamento de Asistencia Técnica de LATICRETE:

Línea telefónica gratuita: 1.800.243.4788, ext. 1235
Teléfono: +1.203.393.0010, ext. 1235
Fax: +1.203.393.1948

Material informativo sobre aspectos técnicos y de seguridad

Para obtener material sobre aspectos técnicos y de seguridad, visite nuestro sitio web en laticrete.com.

10. SISTEMAS ESPECIALES

Podrá obtener más información sobre los productos en nuestro sitio web laticrete.com. A continuación, encontrará una lista de documentos afines:

- DS 230.13: LATICRETE® 1 Year Product Warranty (United States and Canada)
- DS 502.0: NXT® Primer
- DS 503.0: NXT® Embossing Admix

LATICRETE International, Inc.

One LATICRETE Park North, Bethany, CT 06524-3423 USA • 1.800.243.4788 • +1.203.393.0010 • www.laticrete.com

© 2023 LATICRETE International, Inc. All trademarks shown are the intellectual properties of their respective owners.