



STONETECH® Sellador de Uso Intensivo

DS-279E-0624

**Globally Proven
Construction Solutions**



1. NOMBRE DEL PRODUCTO

STONETECH® Sellador de Uso Intensivo

2. FABRICANTE

LATICRETE International, Inc.
1 LATICRETE Park North
Bethany, CT 06524-3423 USA

Teléfono: +1.203.393.0010, ext. 1235

Línea telefónica gratuita: 1.800.243.4788, ext.

1235

Fax: +1.203.393.1684

Sitio de Internet: laticrete.com

3. DESCRIPCIÓN DEL PRODUCTO

STONETECH® Heavy Duty sealer is a water-based penetrating sealer that provides advanced stain and antimicrobial product protection, while preserving the natural look of the surface. It protects against oil and water-based stains on natural stone, tile, masonry, and grout in interior and exterior applications. Built with Microban® antimicrobial protection, STONETECH Heavy Duty Sealer continuously inhibits the growth of stain and odor causing bacteria, mold and mildew on surfaces. A safer alternative to high VOC solvent based sealers that is better for you and the environment and comes with a 25 year product satisfaction guarantee.

Usos

- Countertops
- Backsplashes
- Floors
- Walls

Ventajas

- Offers advanced stain protection
- Built with Microban® antimicrobial technology - Continuously inhibits the growth of bacteria, mold and mildew on the sealed surface.
- Preserves the original look of the surface and is breathable
- Water-based formula - Better for you and the environment
- Low odor, non-flammable and weather resistant - For interior and exterior use
- Professional grade Note: STONETECH Heavy Duty Sealer built with Microban antimicrobial product protection can be combined for use with previous versions of the product to obtain stain protection performance. For antimicrobial product protection, use STONETECH Heavy Duty Sealer with Microban antimicrobial protection.

Sustratos adecuados

Presentación

1/2 l (1 pinta), 0.94 l (1/4 de gal.), 3.78 l (1 gal.), 18.93 l (5 gal.), 208.19 l (55 gal.)

Rendimiento aproximado

- Up to 112 ft²/pint (10.4 m²/473 mL) / single coat
- Up to 225 ft²/quart (20.9m²/946 mL) / single coat
- Up to 900 ft²/gallon (83.6 m²/3.8 L) / single coat
- Up to 4500 ft²/ 5 gal (418 m²/ 18.9 L) / single coat

Precauciones

- Consult SDS for more safety information.
- Storage and Handling Instructions: Avoid prolonged exposure to vapors. Use in a well-ventilated area. Do not ingest. Avoid contact with eyes and skin. KEEP OUT OF THE REACH OF CHILDREN. Do not freeze or store above 100°F (38°C). Do not mix with other chemicals. Do not release to natural waterways.

4. DATOS TÉCNICOS

Información del producto VOC/LEED

<400 g/L (excluding water) for EPA Purposes

<120 g/L (including water) for LEED and U.S. State purposes (Low Solids Coating)

Propiedades físicas

Form	Liquid
Color	Pale Amber
Odor	Mild
pH	9 – 11
Specific Gravity	1.009

Propiedades de trabajo

Full Cure	24 – 72 hours
Surface Traffic	6-8 hours

Las especificaciones están sujetas a cambios sin notificación. Los resultados exhibidos son representativos pero reflejan los procedimientos de prueba utilizados. El desempeño real en el área de trabajo dependerá de los métodos de instalación y de las condiciones del lugar.

5. INSTALACIÓN

Surface Preparation

Read entire label before using. Use only as directed. Always test in a small inconspicuous area with a 24-hour cure time to determine ease of application and desired results. Allow new grout installations to cure for a minimum of 72 hours prior to application. May also be used as a pre-grout sealer. Make sure surface is clean and free of waxes and coatings. Sealer may be applied to damp surfaces one hour after standing water has been removed. Surface temperature should be between 50°F and 80°F (10°C and 27°C). Ensure that the area is well-ventilated during application and until the surface is dry. Keep children and pets out of the area until treated surface is dry.

Application

1. Ensure cap is closed and sealed, and shake well before use.
2. Mask off surfaces not intended to be treated.
3. Liberally apply an even coat of STONETECH® Heavy Duty Sealer using a paint pad, roller, brush or low-pressure sprayer.
4. Allow sealer to penetrate the surface for 10-15 minutes. During this time, keep the surface wet with sealer, adding more sealer as needed. DO NOT ALLOW SEALER TO COMPLETELY DRY ON THE SURFACE.
5. Thoroughly wipe dry the entire surface with clean absorbent towels.
6. A second coat may be needed for porous, absorbent surfaces. If a second coat is required, it should be applied within 30-40 minutes from the initial application as directed in steps 3-5.
7. Should a sealer residue appear, rewet the impacted section of the surface with sealer. Agitate the surface with a white nylon scrubbing pad to loosen residue and wipe dry with a clean, absorbent towel.

8. A full cure is achieved in 24-72 hours. Use of the treated surface may resume in 6-8 hours. If use of the surface must resume sooner, cover the treated surface with red rosin paper to protect it until full cure is achieved.
9. Clean tools used during application with water.

Expected Wear

- Up to 5 years on interior surfaces
 - Up to 3 years on exterior surfaces
- For best results, reapply annually.

6. DISPONIBILIDAD Y COSTO

Disponibilidad

Los materiales LATICRETE® y LATAPOXY® están disponibles en todo el mundo.

Para obtener información sobre los distribuidores, llame a:

Línea telefónica gratuita: 1.800.243.4788
Teléfono: +1.203.393.0010

Para obtener información sobre los distribuidores en Internet, visite LATICRETE en laticrete.com

Costo

Comuníquese con un distribuidor de LATICRETE de su zona.

7. GARANTÍA

Consulte la Sección 10. SISTEMAS ESPECIALES:

8. MANTENIMIENTO

Highly alkaline, acidic, ammoniated, abrasive cleaners are not necessary for daily maintenance and may also degrade the Sealer, adversely affecting stain resistance. Tile and stone routine cleaning with a neutral pH cleaner such as STONETECH Stone & Tile Cleaner is recommended. For tough or difficult to remove soil use STONETECH KlenzAll™ Cleaner, a nylon scrubbing pad or a long handled stiff bristle brush. Please note: Prior to using any cleaning material on a tile, stone, etc. installation, test a discrete area or scrap piece of tile to insure desired results. For additional information, please refer to the TDS 262 Stone and Tile Care Guide.

9. DEPARTAMENTO DE ASISTENCIA TÉCNICA

Asistencia técnica

Para obtener más información, comuníquese con la Línea Directa del Departamento de Asistencia Técnica de LATICRETE:

Línea telefónica gratuita: 1.800.243.4788, ext. 1235
Teléfono: +1.203.393.0010, ext. 1235
Fax: +1.203.393.1948

Material informativo sobre aspectos técnicos y de seguridad

Para obtener material sobre aspectos técnicos y de seguridad, visite nuestro sitio web en laticrete.com.

10. SISTEMAS ESPECIALES

Podrá obtener más información sobre los productos en nuestro sitio web laticrete.com. A continuación, encontrará una lista de documentos afines:

- DS 230.25ST: LATICRETE® Product Warranty
- DS 211.0: STONETECH® Stone & Tile Cleaner
- DS 215.0: STONETECH KlenzAll™ Cleaner
- TDS 262: Stone and Tile Care Guide

LATICRETE International, Inc.

One LATICRETE Park North, Bethany, CT 06524-3423 USA • 1.800.243.4788 • +1.203.393.0010 • www.laticrete.com

© 2024 LATICRETE International, Inc. All trademarks shown are the intellectual properties of their respective owners.