



3701 Lite Mortar

DS-36590E-0723

**Globally Proven
Construction Solutions**



1. NOMBRE DEL PRODUCTO

3701 Lite Mortar

2. FABRICANTE

LATICRETE International, Inc.
1 LATICRETE Park North
Bethany, CT 06524-3423 USA

Teléfono: +1.203.393.0010, ext. 1235

Línea telefónica gratuita: 1.800.243.4788, ext.

1235

Fax: +1.203.393.1684

Sitio de Internet: laticrete.com

3. DESCRIPCIÓN DEL PRODUCTO

3701 Lite Mortar contains carefully selected polymers, portland cement and light weight aggregates. 3701 Lite Mortar does not need a latex admixture. You will only need to add water to produce thick bed mortar or a vertical repair mortar/screed. It contains no respirable crystalline silica levels that exceed the OSHA action level*. 3701 Lite Mortar weighs half the amount of a conventional thick bed mortar and retains the same coverage.

Usos

- Interior and exterior applications
- Horizontal, vertical, overhead applications
- Wet and dry applications
- Bonded and non-bonded thick bed mortar applications
- Conventional thick bed mortar applications
- Concrete repairs

Ventajas

- Light weight - half the weight of conventional mortars
- Excellent for vertical applications such as rendering walls, pools, etc.
- Excellent for overhead applications
- Contains no respirable crystalline silica levels that exceed the OSHA action level*
- Freeze-thaw compliant
- Ease of mixing and application - can be applied up to 3/4" on a vertical surface
- Polymer fortified – no need for latex additives
- Premixed – no job site blending of powders required
- Economical – saves time and money
- For use as a scratch or finish coat in place of Type S or Type N mortar
- Can be used to ramp and pitch areas - bonded mortar bed assembly is possible with a slurry bond coat of LATICRETE 254 Platinum, down to a feather edge * OSHA action level set forth in OSHA's Respirable Crystalline Silica (RCS) standard for construction, 29 CFR 1926.1153, as tested by an independent laboratory to be below the OSHA action level for respirable crystalline silica - laticrete.com/silica

Sustratos adecuados

Presentación

30 lb (13.6 kg) bag; 56 bags per pallet

Part Number: 1060-0030-21

Rendimiento aproximado

Render/Repair	Mortar Bed	Depth
12 sq. ft. (1.1 m ²)	10 sq. ft. (.93 m ²)	½" (13mm)
6 sq. ft. (.56 m ²)	5 sq. ft. (.46 m ²)	1" (25 mm)
4 sq. ft. (.37 m ²)	3 sq. ft. (.28 m ²)	1-½" (38mm)
3 sq. ft. (.28 m ²)	2 sq. ft. (.19 m ²)	2" (51 mm)

Limitaciones

- Use LATAPOXY® 300 Adhesive for installing green marble or moisture sensitive stone, agglomerates, and resin backed tile or stone.

- For veneer installations using this product, consult local building code requirements regarding limitations and installation system specifications.
- Adhesives/mastics, mortars and grouts for ceramic tile, pavers, brick and stone are not replacements for waterproofing membranes. When a waterproofing membrane is required, use a LATICRETE® Waterproofing Membrane (see Section 10 FILING SYSTEMS).
- Surfaces must be structurally sound, stable and rigid enough to support ceramic/stone tile, thin brick and similar finishes. Substrate deflection under all live, dead and impact loads, including concentrated loads, must not exceed L/360 for thin bed ceramic tile/brick installations or L/480 for thin bed stone installations where Data Sheets are subject to change without notice. For latest revision, check our website at www.laticrete.com. DS-100.0-1017 L=span length (except where local building codes specify more stringent deflection requirements)

Precauciones

- Consult SDS for more safety information.
- During cold weather, protect finished work from traffic until fully cured.
- Allow a minimum 14 day cure at 70°F (21°C) after the final grouting period prior to filling water features with water.
- Contains portland cement. Causes severe skin burns and eye damage. Wear protective gloves, protective clothing and eye protection. In case of contact, flush thoroughly with water.
- Do not take internally. Do not breathe dust. Wear a respirator in dusty areas.
- Keep out of reach of children

4. DATOS TÉCNICOS



Propiedades físicas

Testing	Results (Render/Repair)
Compressive Strength (PSI) ASTM C109	1 day = 1000 to 1500 3 day = 2000 to 2500 7 day = 2500 to 3000 28 day = 2500 to 3500
Flexural Strength (PSI) ASTM C348	7 day = 500 to 700
Tensile Strength (PSI) ASTM C1583	28 day = 150 to 200

Testing	Results (Mortar Bed)
Compressive Strength (PSI) ASTM C109	1 day = 2000 to 3500 7 day = 3500 to 4500 28 day = 4000 to 5000
Flexural Strength (PSI) ASTM C348	7 day = 800 to 1000
Tensile Strength (PSI) ASTM C1583	28 day = 150 to 200

Specifications subject to change without notification. Results shown are typical but reflect test procedures used. Actual field performance will depend on installation methods and site conditions.

Propiedades de trabajo

Properties	Time
Initial Set	4 to 6 hours
Final Set	8 to 10 hours
Pot Life	2 hours
Time to Foot Traffic	16 hours
Time to Heavy Traffic	72 hours
Liquid Applied Membrane	72 hours

Las especificaciones están sujetas a cambios sin notificación. Los resultados exhibidos son representativos pero reflejan los procedimientos de prueba utilizados. El desempeño real en el área de trabajo dependerá de los métodos de instalación y de las condiciones del lugar.

5. INSTALACIÓN

Surface Preparation

All surfaces should be between 40°F (4°C) and 90°F (32°C) and structurally sound, clean and free of all dirt, oil, grease, laitance, paint, concrete sealers or curing compounds. Dry dusty concrete slabs or masonry should be dampened and excess water swept off. Installation may be made on a damp surface. Expansion joints shall be provided through the tile work from all construction or expansion joints in the substrate. Follow ANSI specification A108.01-3.7: Requirements for Movement Joints: Preparations by Other Trades” or TCNA detail EJ171 “Movement joints-Vertical & Horizontal”. Do not cover expansion joints with mortar.

Application

Mortar Bed

• **Mixing Mortar Bed—Dry Pack Consistency for Floors**

Mix a 30 lb bag (13.6 kg) of 3701 Lite Mortar with 3.8 to 4.0 qts (3.6 to 3.8 ℓ) of water for 2 to 3 minutes. Mix to a stiff, semi-dry consistency. Allow mortar to slake for 5 minutes. Remix without adding any more water or powder for another 2 to 3 minutes. Mix ratio may vary dependent upon weight of finish.

• **Bonded Mortar Bed—Installation**

Before placing mortar, apply a slurry bond coat made from 254 Platinum or 257 Titanium. While the slurry bond coat is wet, spread the mortar and compact well. If placing tile immediately, apply another slurry bond coat to the surface of the mortar bed (made from either 254 Platinum or 257 Titanium). While the slurry bond coat is wet and sticky, place the tile and beat in well. Refer to TDS 143 "Slurry Bond Coats – When & What to Use" for more information on slurry bond coats.

• **Unbonded Mortar Bed—Installation**

Before placing mortar, place a cleavage membrane (e.g. 4 mil thick polyethylene sheeting or 15 lb, builder felt) on the substrate. Place mortar over the cleavage membrane (approximately 1/2 the depth of the mortar bed). Next, place 2" x 2" (50 mm x 50 mm), 16 gauge galvanized welded wire mesh over the mortar. Then, place the balance of the mortar bed. The wire mesh should be suspended in the middle of the mortar bed. Spread the mortar and compact it well. Minimum mortar bed thickness shall be 2" (50 mm). If placing tile immediately, apply another slurry bond coat to the surface of the mortar bed (made from either 254 Platinum or 257 Titanium). While the slurry bond coat is wet and sticky, place the tile and beat in well.

Wall Renders

• **Mixing Wall Renders**

Mix a 30 lb bag (13.6 kg) of 3701 Lite Mortar with 5.5 to 5.6 qts (5.2 to 5.3 ℓ) of water. Mix to a plastic consistency, 2 to 3 minutes. Allow mortar to slake for 5 minutes. Remix without adding any more water or powder for another 2 to 3 minutes.

• **Wall Renders—Installation**

No slurry bond coat is required prior to placing wall renders. Apply wall render with a steel trowel pressing mortar into good contact with the substrate.

Application thicknesses over 3/4" (19 mm), apply a "scratch coat" first. Scratch mortar before it hardens. After "scratch coat" hardens, apply the "brown or float coat" working the mortar into good contact with the scratch coat. Do not exceed 3/4" (19 mm) thickness per lift. Scratch all lifts that will receive additional float coats. Float wall with steel trowel and straight edges to form a plumb and true mortar surface. Allow the completed

render coats to cure for 24 hours at 70°F (21° C) prior to the installation of tile.

Concrete Repair

• **Concrete Repair and Resurfacing – Installation**

Mix a 30 lb bag (13.6 kg) of 3701 Lite Mortar with 5.5 to 5.6 qts (5.2 to 5.3 ℓ) of water. Mix to a plastic consistency, 2 to 3 minutes. Allow mortar to slake for 5 minutes. Remix without adding any more water or powder for another 2 to 3 minutes.

Before placing mortar, apply a slurry bond coat made from 254 Platinum or 257 Titanium to all reinforcing steel and existing clean, sound and stable concrete surfaces. Prior to placing the mortar. While the slurry bond coat is wet and sticky place the topping mortar. Compact the surface of the mortar with a flat trowel and ensure all voids are filled. Avoid over troweling.

• **Cold Weather Note**

The setting of portland cement mortars and grouts are retarded by low temperatures. Protect finished work for an extended period when installing in cold weather.

• **Hot Weather Note**

The evaporation of moisture in portland cement mortars is accelerated by hot, dry conditions. Apply mortar to dampened surfaces and protect freshly spread mortar and finished work when installing in temperatures over 90°F (32°C). Note: A slurry bond coat should also be applied to the edges of mortar beds installed from previous work periods. Cleaning Clean tools and tile work with water while the mortar is fresh.

6. DISPONIBILIDAD Y COSTO

Disponibilidad

Los materiales LATICRETE® y LATAPOXY® están disponibles en todo el mundo.

Para obtener información sobre los distribuidores, llame a:

Línea telefónica gratuita: 1.800.243.4788
Teléfono: +1.203.393.0010

Para obtener información sobre los distribuidores en Internet, visite LATICRETE en laticrete.com

Costo

Comuníquese con un distribuidor de LATICRETE de su zona.

7. GARANTÍA

Consulte la Sección 10. SISTEMAS ESPECIALES:

- 1 Year Product Warranty (US - English)
- 5 Year System Warranty (US - English)
- 10 Year System Warranty (US - English)
- 25 Year System Warranty (US - English)
- LATICRETE Lifetime System Warranty (US - English)

9. DEPARTAMENTO DE ASISTENCIA TÉCNICA

Asistencia técnica

Para obtener más información, comuníquese con la Línea Directa del Departamento de Asistencia Técnica de LATICRETE:

Línea telefónica gratuita:

1.800.243.4788, ext. 1235

Teléfono: +1.203.393.0010, ext.
1235

Fax: +1.203.393.1948

Material informativo sobre aspectos técnicos y de seguridad

Para obtener material sobre aspectos técnicos y de seguridad, visite nuestro sitio web en laticrete.com.

LATICRETE International, Inc.

One LATICRETE Park North, Bethany, CT 06524-3423 USA • 1.800.243.4788 • +1.203.393.0010 • www.laticrete.com

© 2023 LATICRETE International, Inc. All trademarks shown are the intellectual properties of their respective owners.