



SPECTRALOCK® 2000 IG Juntas Grado Industrial

DS-30E-0125

**Globally Proven
Construction Solutions**



1. NOMBRE DEL PRODUCTO

SPECTRALOCK® 2000 IG Juntas Grado Industrial

2. FABRICANTE

LATICRETE International, Inc.
1 LATICRETE Park North
Bethany, CT 06524-3423 USA

Teléfono: +1.203.393.0010, ext. 1235

Línea telefónica gratuita: 1.800.243.4788, ext.

1235

Fax: +1.203.393.1684

Sitio de Internet: laticrete.com

3. DESCRIPCIÓN DEL PRODUCTO

SPECTRALOCK 2000 IG is a highly chemical resistant industrial grade epoxy grout for: ceramic tile, pavers, floor brick, packing house tile, and stone. SPECTRALOCK 2000 IG is supplied as factory proportioned kits consisting of epoxy resin, hardener, and silica filler.

Equipped with Microban Anti-Microbial Protection

SPECTRALOCK 2000 IG #2 Unit Pail with #22 Midnight Black (2000-SL0001-23)

This product is recommended and designed for use in installations where the highest chemical resistance is necessary. These would include areas where there is heavy use of no-rinse cleaners, commonly known as "back-of-house" installations such as commercial kitchens. This product uses SPECTRALOCK #22 Midnight Black Part C Powder only (Included in pail).

SPECTRALOCK 2000 IG Grey #2 Unit Pail (2000-SL0001-21) and #4 Commercial Unit liquids (S-2000C-SL-03 / S-2000P-SL-03)

These products are recommended to be used within applications such as; commercial "front-of-house" and other general commercial and industrial type projects. These products can be used with ALL LATICRETE SPECTRALOCK Grout Part C Powders (except #44 Bright White).

Usos

- Use in corrosive environments such as:
- Industrial—bakeries, dairies, cheese factories, breweries, CIP rooms, meat packing plants, soft drink plants, confectioneries, canneries, distilleries, pharmaceutical factories, veterinary hospitals, clinics and kennels.
- Commercial—institutional kitchens, fast food restaurants, cafeterias, laboratories, supermarkets.

Ventajas

- High chemical resistance
- Improved temperature resistance
- Maximum physical strength
- Equipped with anti-microbial technology to protect the treated article.
- Highly resistant to bacteria attack
- Exceeds ANSI 118.3 (Epoxy) and ANSI 118.5 (Furan) performance requirements
- Water cleanable
- Fast curing
- Cures at low temperature

Sustratos adecuados

Presentación

- Unidad N.º 2: juego de cubetas (unidad completa, gris y negro)
 - Peso neto de la unidad: 12.96 kg (28.5 lb)
- Unidad N.º 2: cubetas (líquido solamente)
 - Peso neto de la unidad: 4.8 kg (10.5 lb)
- Unidad N.º 4: cajas (líquido solamente)
 - Peso de la unidad: 7.3 kg (16 lb)

Limitaciones

- SPECTRALOCK 2000 IG #2 Unit Pail with #22 Midnight Black (2000-SL0001-23) This product is

recommended and designed for use in installations where the highest chemical resistance is necessary. These would include areas where there is heavy use of no-rinse cleaners, commonly known as "back-of-house" installations such as commercial kitchens. This product uses SPECTRALOCK #22 Midnight Black Part C Powder only (Included in pail). SPECTRALOCK 2000 IG Grey #2 Unit Pail (2000-SL0001-21) and #4 Commercial Unit liquids (S-2000C-SL-03 / S-2000P-SL-03) These products are recommended to be used within applications such as; commercial "front-of-house" and other general commercial and industrial type projects. These products can be used with ALL LATICRETE SPECTRALOCK Grout Part C Powders (except #44 Bright White).

- Maximum chemical resistance is achieved in seven (7) days at 70°F (21°C). Protect from exposure to strong chemicals until fully cured; at colder temperatures it takes longer to achieve full cure.
- For interior use only.
- Grouts for ceramic tile, pavers, brick and stone are not replacements for waterproofing membranes. When a waterproofing membrane is required, use a LATICRETE® Waterproofing Membrane (see Section 10 FILING SYSTEM).
- Please consult with LATICRETE Technical Services for specific recommendations, if grout will be exposed to chemicals other than those indicated on the chemical resistant chart.
- LATICRETE recommends using the #2 2000IG liquids with #22 BLACK SPECTRALOCK powder for all back-of-house / commercial restaurant installations where the use of enzymatic cleaners is common. For all other installations the #4 units can be used with all colors (except bright white).

Precauciones

- SPECTRALOCK 2000 IG #2 Unit Pail with #22 Midnight Black (2000-SL0001-23) This product is recommended and designed for use in installations where the highest chemical resistance is necessary. These would include areas where there is heavy use of no-rinse cleaners, commonly known as "back-of-house" installations such as commercial kitchens. This product uses SPECTRALOCK #22 Midnight Black Part C Powder only (Included in pail). SPECTRALOCK 2000 IG Grey #2 Unit Pail (2000-SL0001-21) and #4 Commercial Unit liquids (S-2000C-SL-03 / S-2000P-SL-03) These products are recommended to be used within applications such as; commercial "front-of-house" and other general commercial and industrial type projects. These products can be used with ALL LATICRETE SPECTRALOCK Grout Part C Powders (except #44 Bright White). Consult SDS for more safety information.
- Protect finished work from chemical exposure, dirt and traffic until fully cured.

- See MAINTENANCE (Section 8) for care, cleaning, maintenance and warranty requirements.
- Until cured, SPECTRALOCK 2000 IG could cause skin burns and eye damage. Wear protective gloves, protective clothing, and eye protection. In case of contact, flush thoroughly with water.
- Do not take internally. Silica sand may cause cancer, respiratory irritation or serious lung problems. Do not breathe dust. Wear a respirator in dusty areas.
- Because propane gas heaters will cause epoxy grouts to yellow, refrain from using such heaters or properly vent all exhaust.
- Keep out of reach of children.
- Epoxy Resins may affect the color of white or porous stones (such as White Carrara, Thassos white, royal Danby, etc.).
- Test stones for compatibility with water and cleaning additive mixture
- Conduct a test area to determine compatibility with metal or steel tile

4. DATOS TÉCNICOS

Información del producto VOC/LEED

This product has been certified for Low Chemical Emissions (ULCOM/GG UL2818) under the UL GREENGUARD Certification Program for Chemical Emissions for Building Materials, Finishes and Furnishings (UL 2818 Standard) by UL Environment

Propiedades físicas



Registration #143530

NSF Registration assures inspection officials and end users that formulation and labels meet appropriate food safety regulation. NSF International launched its voluntary Non-food Compounds Registration Program in 1999 to re-introduce the previous authorization program administered by the U.S. Department of Agriculture (USDA).

EVALUATION PER ANSI A118.3		
PROPERTY	VALUE	
TEST/ NO.	EVALUATION	REQUIREMENT
Water Cleanability (E5.1)	Pass	80 min.
Initial Setting Time (E5.2)	Pass	> 2.0 hrs.
Service Setting Time (E5.2)	Pass	< 7 days
Shrinkage (E5.3)	0.07%	< 0.25%
Sag (E5.4)	Pass	no change
Quarry Shear Bonds (E5.5)	2200 PSI (15.2 MPa)*	> 1000 psi (6.9 MPa)
Compressive Strength (E5.6)	8300 PSI (57.2 MPa)	> 3500 psi (24 MPa)
Tensile Strength (E5.7)	3000 PSI (20.7 MPa)	> 1000 psi (6.9 MPa)
Thermal Shock (E5.8)	2100 PSI (14.5 MPa)	> 500 psi (3.4 MPa)

* Tile Failed During Test TCA-061-93

EVALUATION PER ANSI A118.5			
Property	Test Method	Evaluation	Grout Requirement
Compressive Strength	ASTM C579	9255 PSI (63.8 MPa)	3000 psi (21 MPa)
Tensile Strength	ASTM C307	2672 PSI (18.4 MPa)	400 psi (2.75 MPa)
Absorption	ASTM C413	0.19%	Max. 1%
Modulus of Rupture	ASTM C580	5300 psi (37 MPa)	600 psi (4.1 MPa)
Initial Set, Hours	ASTM C308	2	Max 5
Final Set, Days	ASTM C308	6	Max 7
Linear Shrinkage	ASTM C531	0.07%	Max. 1%
Working Time Minutes	ASTM C308	80	Min. 10
Bond Strength	ASTM C321	Pass**	150 psi (1 MPa)

** Brick Failed During Test

SERVICE TEMPERATURE RANGE***	
Intermittent Exposure	up to 360°F/182°C
Constant Exposure	up to 185°F/80°C

***Service Temperature Exposure defined as:
Intermittent—where hot materials, liquids or steam come in contact with grout for a short time.

Constant—where grout is subjected to continuous heat such as under a bakery oven.

Time to Traffic

CURE TIME			
FLOOR TEMPERATURE	TIME TO LIGHT TRAFFIC [^]	TIME TO HEAVY TRAFFIC ^{^^}	FULL CURE ^{^^^}
50°F (10°C)	20 Hours	32 Hours	8 - 10 Days
60°F (16°C)	11 Hours	24 Hours	7 Days
70°F (21°C)	8 Hours	16 Hours	7 Days

[^] Foot Traffic

^{^^} Place Equipment

^{^^^} Exposure to Chemical and Heat

Propiedades de trabajo (70°F [21°C])

Working Time	80 minutes
Wet Density	12.2 lb/gal (1.5g/mL)

Resistencia química

Chemical Resistance ¹ Chart at 70°F (21°C)			
Chemical Name	Continuous Exposure	Intermittent Exposure	Splash Exposure
Food Acids			
Lactic to 10%	R	R	R
Acetic to 10%	R	R	R
Formic to 5%	R	R	R
Citric to 50%	R	R	R
Tartaric to 50%	R	R	R
Tannic to 50%	R	R	R
Oleic to 100%	R	R	R
Phosphoric to 80%	R	R	R
Mineral Acids			
Hydrofluoric acid ² 10%	R	R	R
Sulfuric to 50% ²	R	R	R
Nitric to 30% ²	R	R	R
Hydrochloric to ² 36.5%	R	R	R
Corrosive Cleaners			
Sodium Hypochlorite ² (Bleach) 3%	R	R	R
Sodium Hydroxide (Saturated)	R	R	R
Solvents			
Xylene	R	R	R
Ethyl Alcohol	R	R	R
Mineral Spirits	R	R	R
Toluene	R	R	R
Methylene Chloride	NR	NR	NR
Gasoline	R	R	R

¹Chemical Resistance defined as:

Splash—minor spill wiped up quickly such as in a laboratory.

Intermittent—Exposure to chemicals where clean up takes place several times a day such as in a commercial kitchen.

Continuous—heavy exposure to chemicals where clean up is less frequent such as in an industrial food plant.

R=Recommended, NR=Not Recommended. Chemical Resistance determined in accordance with ASTM C267. ²Long Exposure will cause color change. Specifications subject to change without notification. Results shown are typical but reflect test procedures used. Actual field performance will depend on installation methods and site conditions.

Las especificaciones están sujetas a cambios sin notificación. Los resultados exhibidos son representativos pero reflejan los procedimientos de prueba utilizados. El desempeño real en el área de trabajo dependerá de los métodos de instalación y de las condiciones del lugar.

5. INSTALACIÓN

Refer to SPECTRALOCK® 2000 IG How to Install Guide DS 004.5 for more information.

Surface Preparation

Before starting to grout remove spacers and debris in grout joints and remove dust and dirt using a damp sponge. Allow to dry. Do not leave water standing in joints. Do not clean tiles with acid cleaners. Substrate temperature must be between 45°F (7°C) and 90°F (32°C).

Note: Temperature will affect working properties of SPECTRALOCK 2000 IG. Warm temperatures will speed curing and shorten working time. Cool temperatures will slow curing and require longer time to traffic. Store SPECTRALOCK 2000 IG (including Part C) at 70°F (21°C) for 24 hours prior to use.

Mixing

Pour SPECTRALOCK 2000 IG Part A and Part B into a clean mixing pail and mix thoroughly with a drill mixer until liquids are completely blended. Add all of the Part C powder. The mix will look thick at the beginning. Whip it thoroughly with high speed mixer (>450 rpm) until uniformly blended (Minimum 2 Minutes). This will aerate the grout to a very fluffy mix.

Application

For maximum pot life, remove grout from bucket and spread on floor or plastic sheeting. Spread the grout with sharp, firm rubber grout float. Work the grout paste into the joints. Insure the joint is filled and grout is not sitting on top. Remove excess grout from the face of the tiles with the edge of the grout float. Hold the float at 90° angle and pull it diagonally across the joints and tile to avoid pulling out the material.

Initial Cleaning – USE INITIAL WASH CLEANING ADDITIVE.

Once grout has been spread, wait approximately 30 minutes at 70°F (21°C) prior to beginning initial wash. Add Initial Wash cleaning additive to 2 gals (7.6 L) of clean water and mix until fully dissolved. Do not mix cleaning additive with grout. Wipe grout joints and tile surface with a white nylon pad and plenty of water (with the cleaning additive) using a circular motion. Drag a

damp clean sponge diagonally over the scrubbed surface to remove grout residue.

Final Cleaning – USE FINAL WASH CLEANING ADDITIVE.

Wait at least 90 minutes after the initial wash at 70°F (21°C) for the final wash using the same procedure as in the initial wash. Prepare another two gallons of clean water and add the Final Wash cleaning additive and mix until fully dissolved. In the final wash avoid contact with the grout – clean tile surface only.

6. DISPONIBILIDAD Y COSTO

Disponibilidad

Los materiales LATICRETE® y LATAPOXY® están disponibles en todo el mundo.

Para obtener información sobre los distribuidores, llame a:

Línea telefónica gratuita: 1.800.243.4788
Teléfono: +1.203.393.0010

Para obtener información sobre los distribuidores en Internet, visite LATICRETE en laticrete.com

Costo

Comuníquese con un distribuidor de LATICRETE de su zona.

7. GARANTÍA

Consulte la Sección 10. SISTEMAS ESPECIALES:

- 10 Year Commercial Kitchen Industrial Application System Warranty (US) (English)
- 25 Year System Warranty (US) (English)
- 1 Year Product Warranty (US) (English)

8. MANTENIMIENTO

- All stone and tile should be maintained and sealed with LATICRETE® STONETECH® professional products as appropriate for the specific tile/stone and installation situation.
- Rinsing of cleaner residue and debris with a clean water rinse is required to maintain product and systems warranty.
- Rinse fatty acid residue from grout and tile surface to avoid potential grout deterioration caused by prolonged exposure.
- Protect surfaces from common stains by using a STONETECH Bulletproof Sealer.
- Routine maintenance should follow with STONETECH Revitalizer® Cleaner and Protector or a neutral pH cleaner such as STONETECH Stone & Tile Cleaner.
- For tough or difficult to remove soil use STONETECH KlenzAll Cleaner, a nylon scrubbing pad or a long handled stiff bristle brush.
- For additional information, please refer to the TDS 400 Grout Guide.

9. DEPARTAMENTO DE ASISTENCIA TÉCNICA

Asistencia técnica

Para obtener más información, comuníquese con la Línea Directa del Departamento de Asistencia Técnica de LATICRETE:

Línea telefónica gratuita:

1.800.243.4788, ext. 1235

Teléfono: +1.203.393.0010, ext.
1235

Fax: +1.203.393.1948

Material informativo sobre aspectos técnicos y de seguridad

Para obtener material sobre aspectos técnicos y de seguridad, visite nuestro sitio web en laticrete.com.

10. SISTEMAS ESPECIALES

Podrá obtener más información sobre los productos en nuestro sitio web laticrete.com. A continuación, encontrará una lista de documentos afines:

- DS 230.13: LATICRETE® Product Warranty
- DS 230.10IG: LATICRETE 10 Year Commercial/Industrial Kitchen System Warranty (United States and Canada)
- DS 236.0: 9235 Waterproofing Membrane
- DS 663.0: HYDRO BAN®
- DS 004.5: SPECTRALOCK® 2000 IG How to Install

United States Invention Patent No.: 6,784,229 (and other Patents)

LATICRETE International, Inc.

One LATICRETE Park North, Bethany, CT 06524-3423 USA • 1.800.243.4788 • +1.203.393.0010 • www.laticrete.com

© 2025 LATICRETE International, Inc. All trademarks shown are the intellectual properties of their respective owners.