

## **L&M™ LUMISEAL FX™**

DS-172.5-0524

# Globally Proven Construction Solutions



## 1. PRODUCT NAME

L&M™ LUMISEAL FX™

#### 2. MANUFACTURER

LATICRETE International, Inc. 1 LATICRETE Park North Bethany, CT 06524-3423 USA

Telephone: +1.203.393.0010, ext. 1235 Toll Free: 1.800.243.4788, ext. 1235

Fax: +1.203.393.1684 Website: laticrete.com

## 3. PRODUCT DESCRIPTION

LUMISEAL FX is a high solids, water-based, non-yellowing, blush resistant curing and sealing compound. When used as a sealer, LUMISEAL FX is designed to provide an attractive medium gloss finish on concrete substrates. LUMISEAL FX is formulated with advanced, self-crosslinking emulsion chemistry, providing a very durable film and excellent early water-resistance to whitening or blistering. LUMISEAL FX is suitable for use on interior, exterior, horizontal and vertical surfaces.

## **Specification Description**

03 39 13: Acrylic Curing Compound: Minimum 25% acrylic solids shall conform to ASTM C309, Type 1.

#### Uses

 LUMISEAL FX is recommended to seal new and old concrete surfaces including decorative, colored, and stamped concrete. Other applications include exposed aggregate, brick pavers, polished concrete and other concrete surfaces where a durable gloss and stain resistant sealer is required.

## **Advantages**

- · Non-blushing formula; resists whitening
- Non-yellowing, pure acrylic formulation
- · Resists black tire marks
- · Low odor
- Use on any clean concrete surface
- · Medium gloss
- · Versatile indoor and outdoor use

#### **Suitable Substrates**

- Existing Concrete
- Freshly Poured Concrete

## **Packaging**

1 Gal (3.8 L) 5 Gal (19 L) 55 Gal (208 L)

## **Approximate Coverage**

Surface porosity determines coverage rate. For best results:

First coat, - 200-400 ft²/gal (4.9 to 9.8 m²/L) Second coat, - 400-600 ft²/gal (9.8 to 14.7 m²/L) Decorative concrete - 300 ft²/gal (7.3 m²/L)

Top coat for polished concrete: 800-1,000 ft²/gal (20 to 25 m²/liter)

## Shelf Life

Containers are to be kept tightly sealed. Do not freeze. Store above 40°F (4°C). Stir well before using as some settlement will occur during storage. Shelf life is one year in factory-sealed containers when properly stored.

#### Limitations

- Heavy applications should be avoided for proper film formation.
- For proper film development, apply only when the surface temperature is over 40(F (4(C) and the relative humidity is below 80%.

#### **Cautions**

- Use with adequate ventilation
- · Avoid contact with skin, eyes and clothing
- Wear skin and eye protection
- · Wash thoroughly after handling
- · Do not take internally
- Enhanced air circulation is desired to improve the drying rate and to remove organic solvent vapors
- Review Safety Data Sheet (SDS) for product safety information
- Mock-ups and field test areas are required in order to validate performance and appearance related characteristics (including but not limited to color, inherent surface variations, wear, anti-dusting, abrasion resistance, chemical resistance, stain resistance, coefficient of friction, etc.) to ensure system performance as specified for the intended use, and to determine approval of the decorative flooring system.

#### 4. TECHNICAL DATA

#### **Applicable Standard**

• ASTM C 309, Type 1

**Physical Properties** 

Property	Observed
Solids	25%
Alkali Resistance (number of hours, Method #6081,minimum)	>75 hours
Salt Spray 5% Resistance	>750 hours
Dry Time, set to touch	60 minutes
Surface Gloss (2 Coats)	Medium/High
Ultraviolet Resistance (2500 angstrom lamp), 1000 hrs.	0 (Excellent)
VOC	<120 g/L
Color	Milky white liquid, dries clear

Specifications subject to change without notification. Results shown are typical but reflect test procedures used. Actual field performance will depend on installation methods and site conditions.

## **5. INSTALLATION**

## • Freshly placed concrete

Surface must be finished to specified requirements prior to the application of LUMISEAL FX™. Apply one uniform coat with low pressure spray and roller after surface water glaze has disappeared. Do not dilute or puddle. A second sealing coat may be applied any time afterward. Apply to freshly poured concrete after surface water has evaporated. Too much surface water can be detrimental to proper film formation.

## **Existing Concrete**

Surface must be degreased and cleaned of all contaminants with CITREX™ prior to the application of LUMISEAL FX. Dilute with 25-50% water before applying to polished concrete. After dry, apply one or two uniform coats using a microfiber applicator, without puddling, as needed. Allow first coat to dry 2-3 hours before applying the second coat. Dry to the touch in 1 hour. Can be ready for foot traffic in 12 hours. When re-sealing driveways, recommended wait time is 24 hours for vehicular traffic. May require additional coats.

**NOTE:** LUMISEAL FX can be applied as a topical sealer on FGS PERMASHINE polished concrete.

## Cleaning

Clean applicator equipment with water before sealer dries. After it dries, use aromatic solvent.

## 6. AVAILABILITY AND COST

## **Availability**

LATICRETE materials are available worldwide.

## For Distributor Information, Call:

Toll Free: 1.800.243.4788 Telephone: +1.203.393.0010

For on-line distributor information, visit LATICRETE at

laticrete.com

## Cost

Contact a LATICRETE Distributor in your area.

## 7. WARRANTY

See 10. FILING SYSTEM:

## 8. MAINTENANCE

The long term performance, appearance, and life expectancy of surface sealing products are critically dependent upon a good routine maintenance program designed specifically for the installed sealer type, traffic, and other conditions. Properly placed walk-off mats, inside and outside will help increase the life of the floor. Some cleaning products and equipment or improper use of products can damage a wear surface appearance over time. Reapplication may be necessary in heavy traffic areas with greater frequency.

## 9. TECHNICAL SERVICES

## **Technical Assistance**

Information is available by calling the LATICRETE Technical Service Hotline:

Toll Free: 1.800.243.4788, ext. 1235 Telephone: +1.203.393.0010, ext. 1235

Fax: +1.203.393.1948

## **Technical and Safety Literature**

To acquire technical and safety literature, please visit our website at <a href="Iaticrete.com">Iaticrete.com</a>.

## **10. FILING SYSTEM**

Additional product information is available on our website at <u>laticrete.com</u>. The following is a list of related documents:

- DS 230.13: LATICRETE Product Warranty
- DS 176.6: CITREX