



209 Mortero para Pisos

DS-209E-0823

**Globally Proven
Construction Solutions**



1. NOMBRE DEL PRODUCTO

209 Mortero para Pisos

2. FABRICANTE

LATICRETE International, Inc.
1 LATICRETE Park North
Bethany, CT 06524-3423 USA

Teléfono: +1.203.393.0010, ext. 1235

Línea telefónica gratuita: 1.800.243.4788, ext.

1235

Fax: +1.203.393.1684

Sitio de Internet: laticrete.com

3. DESCRIPCIÓN DEL PRODUCTO

209 Floor Mud is a factory prepared blend of high strength portland cement and carefully graded sand. This dry mix is used with water to make semi-dry conventional floor mortar beds. 209 Floor Mud is suitable for interior applications wherever a traditional mortar bed is required under ceramic tile, and ideal for small shower pan fills in bathrooms. Mix with 3701 Mortar Admix for added strength and adhesion properties.

Usos

- Mortar beds
- Leveling beds
- Shower pans

Ventajas

- Pre-mixed - no job site blending of powders required
- Compressive strength
- Economical - saves time and money
- Packaging - plastic vs traditional paper
- Consistency and ease of use

Sustratos adecuados

Presentación

Bolsa de 27 kg (60 lb)

Rendimiento aproximado

Thickness	Coverage
1" thickness (25 mm)	Approximately 6 sq. ft. (0.56 m ²)

- per 60 lb (27 kg) bag

Limitaciones

- Surfaces must be structurally sound, stable and rigid enough to support ceramic/stone tile, thin brick and similar finishes. Substrate deflection under all live, dead and impact loads, including concentrated loads, must not exceed L/360 for thin bed ceramic tile/brick installations or L/480 for thin bed stone installations where L=span length.
- Interior use only

Precauciones

- Consult SDS for more safety information.
- During cold weather, protect finished work from traffic until fully cured.
- Contains portland cement and silica sand. Causes severe skin burns and eye damage. Wear protective gloves, clothing and face protection.
- Do not take internally. Silica sand may cause cancer, respiratory irritation or serious lung problems. Do not breathe dust. Wear a respirator in dusty areas.
- Use LATAPOXY® 300 Adhesive for installing green marble or water sensitive stone and agglomerates.
- Keep out of reach of children.
- Hot Weather Note: The evaporation of moisture in portland cement mortars is accelerated by hot, dry conditions. Apply to dampened surfaces and protect freshly spread mortar and finished work when installing in temperatures over 95°F (35°C).

4. DATOS TÉCNICOS

Propiedades físicas

Test/Test Method	209 mixed with Water	209 mixed with 3701 Admix
28 day Compressive Strength ASTM C270	2050 to 2600 psi (14.1 to 17.9 MPa)	2250 to 2850 psi (15.5 to 19.6 MPa)

- Can be mixed with 3701 Mortar Admix or water
- Temperature: 70°F (21°C)

Propiedades de trabajo

Pot Life	1 hour
Time to Traffic	12 hours
Time to Heavy Traffic	72 hours

- Mixed with 3701 Mortar Admix or water
- Temperature: 70°F (21°C)

Las especificaciones están sujetas a cambios sin notificación. Los resultados exhibidos son representativos pero reflejan los procedimientos de prueba utilizados. El desempeño real en el área de trabajo dependerá de los métodos de instalación y de las condiciones del lugar.

5. INSTALACIÓN

Preparation

All surfaces should be between 40°F (4°C) and 95°F (35°C) and structurally sound, clean and free of all dirt, oil and grease. Dry, dusty concrete slabs should be dampened and excess water swept off. Installation may be made on a damp surface. Do not cover expansion joints with mortar.

Mixing

Mortar Bed use approximately:

3701 Mortar Admix or Water	209 Floor Mud
0.7 gal (2.7 L)	60 lbs (27.3 kg)
1.0 gal (3.8 L)	85 lbs (38.6 kg)
5.0 gal (19 L)	420 lbs (190.9 kg)

- Mix to a stiff, semi-dry consistency
- Refer to bag for mixing hints

Application

Before placing mortar, apply a slurry bond coat made from either 254 Platinum, 257 Titanium or Multimax Lite. While the slurry bond coat is wet, spread the mortar and compact well. If placing tile immediately, apply a slurry bond coat of either 254 Platinum, 257 Titanium or Multimax Lite to the mortar. While the slurry bond coat is wet and sticky, place the tile and beat in well.

Cleaning

Clean tools and tile work with water while mortar is fresh.

6. DISPONIBILIDAD Y COSTO

Disponibilidad

Los materiales LATICRETE® y LATAPOXY® están disponibles en todo el mundo.

Para obtener información sobre los distribuidores, llame a:

Línea telefónica gratuita: 1.800.243.4788
Teléfono: +1.203.393.0010

Para obtener información sobre los distribuidores en Internet, visite LATICRETE en laticrete.com

Costo

Comuníquese con un distribuidor de LATICRETE de su zona.

7. GARANTÍA

Consulte la Sección 10. SISTEMAS ESPECIALES:

- 1 Year Product Warranty (US - English)
- 5 Year System Warranty (US - English)
- 10 Year System Warranty (US - English)

8. MANTENIMIENTO

LATICRETE and LATAPOXY grouts require routine cleaning with a neutral pH soap and water. All other LATICRETE and LATAPOXY materials require no maintenance but installation performance and durability may depend on properly maintaining products supplied by other manufacturers.

9. DEPARTAMENTO DE ASISTENCIA TÉCNICA

Asistencia técnica

Para obtener más información, comuníquese con la Línea Directa del Departamento de Asistencia Técnica de LATICRETE:

Línea telefónica gratuita: 1.800.243.4788, ext. 1235
Teléfono: +1.203.393.0010, ext. 1235
Fax: +1.203.393.1948

Material informativo sobre aspectos técnicos y de seguridad

Para obtener material sobre aspectos técnicos y de seguridad, visite nuestro sitio web en laticrete.com.

10. SISTEMAS ESPECIALES

Podrá obtener más información sobre los productos en nuestro sitio web laticrete.com. A continuación, encontrará una lista de documentos afines:

- DS 230.13: LATICRETE Product Warranty
- DS 231.0: 3701 Mortar Admix
- DS 633.0: LATAPOXY 300 Adhesive
- DS 677.0: 254 Platinum
- DS 34082 : Multimax Lite'
- DS 292 : 257 Titanium

LATICRETE International, Inc.

One LATICRETE Park North, Bethany, CT 06524-3423 USA • 1.800.243.4788 • +1.203.393.0010 • www.laticrete.com

© 2023 LATICRETE International, Inc. All trademarks shown are the intellectual properties of their respective owners.