



# 209 Boue pour planchers

DS-209F-0823

**Globally Proven  
Construction Solutions**



## 1. NOM DU PRODUIT

209 Boue pour planchers

## 2. FABRICANT

LATICRETE International, Inc.

1 LATICRETE Park North

Bethany, CT 06524-3423 États-Unis

Téléphone: +1.203.393.0010, poste 1235

Numéro sans frais: 1.800.243.4788, poste 1235

Télécopieur: +1.203.393.1684

Site Web: [laticrete.com](http://laticrete.com)

## 3. DESCRIPTION DU PRODUIT

209 Floor Mud is a factory prepared blend of high strength portland cement and carefully graded sand. This dry mix is used with water to make semi-dry conventional floor mortar beds. 209 Floor Mud is suitable for interior applications wherever a traditional mortar bed is required under ceramic tile, and ideal for small shower pan fills in bathrooms. Mix with 3701 Mortar Admix for added strength and adhesion properties.

### Utilisation

- Mortar beds
- Leveling beds
- Shower pans

### Avantages

- Pre-mixed - no job site blending of powders required
- Compressive strength
- Economical - saves time and money
- Packaging - plastic vs traditional paper
- Consistency and ease of use

### Supports Appropriés

### Conditionnement

Sac de 27 kg (60 lb)

### Couverture approximative

Thickness	Coverage
1" thickness (25 mm)	Approximately 6 sq. ft. (0.56 m <sup>2</sup> )

- per 60 lb (27 kg) bag

### Restrictions

- Surfaces must be structurally sound, stable and rigid enough to support ceramic/stone tile, thin brick and similar finishes. Substrate deflection under all live, dead and impact loads, including concentrated loads, must not exceed L/360 for thin bed ceramic tile/brick installations or L/480 for thin bed stone installations where L=span length.
- Interior use only

### Mises en garde

- Consult SDS for more safety information.
- During cold weather, protect finished work from traffic until fully cured.
- Contains portland cement and silica sand. Causes severe skin burns and eye damage. Wear protective gloves, clothing and face protection.
- Do not take internally. Silica sand may cause cancer, respiratory irritation or serious lung problems. Do not breathe dust. Wear a respirator in dusty areas.
- Use LATAPOXY® 300 Adhesive for installing green marble or water sensitive stone and agglomerates.
- Keep out of reach of children.
- Hot Weather Note: The evaporation of moisture in portland cement mortars is accelerated by hot, dry conditions. Apply to dampened surfaces and protect freshly spread mortar and finished work when installing in temperatures over 95°F (35°C).

## 4. DONNÉES TECHNIQUES

### Propriétés physiques

Test/Test Method	209 mixed with Water	209 mixed with 3701 Admix
28 day Compressive Strength ASTM C270	2050 to 2600 psi (14.1 to 17.9 MPa)	2250 to 2850 psi (15.5 to 19.6 MPa)

- Can be mixed with 3701 Mortar Admix or water
- Temperature: 70°F (21°C)

### Propriétés d'utilisation

Pot Life	1 hour
Time to Traffic	12 hours
Time to Heavy Traffic	72 hours

- Mixed with 3701 Mortar Admix or water
- Temperature: 70°F (21°C)

Caractéristiques sous réserve de modification sans préavis. Les résultats présentés sont typiques, mais ils reflètent les procédures d'essai utilisées. Les performances réelles sur le terrain dépendent des méthodes de pose et des conditions locales.

## 5. POSE

### Préparation

All surfaces should be between 40°F (4°C) and 95°F (35°C) and structurally sound, clean and free of all dirt, oil and grease. Dry, dusty concrete slabs should be dampened and excess water swept off. Installation may be made on a damp surface. Do not cover expansion joints with mortar.

### Mixing

Mortar Bed use approximately:

3701 Mortar Admix or Water	209 Floor Mud
0.7 gal (2.7 L)	60 lbs (27.3 kg)
1.0 gal (3.8 L)	85 lbs (38.6 kg)
5.0 gal (19 L)	420 lbs (190.9 kg)

- Mix to a stiff, semi-dry consistency
- Refer to bag for mixing hints

### Application

Before placing mortar, apply a slurry bond coat made from either 254 Platinum, 257 Titanium or Multimax Lite. While the slurry bond coat is wet, spread the mortar and compact well. If placing tile immediately, apply a slurry bond coat of either 254 Platinum, 257 Titanium or Multimax Lite to the mortar. While the slurry bond coat is wet and sticky, place the tile and beat in well.

### Cleaning

Clean tools and tile work with water while mortar is fresh.

## 6. DISPONIBILITÉ ET COÛT

### Disponibilité

Les produits LATICRETE® et LATAPOXY® sont proposés dans le monde entier.

### Appeler un des numéros suivants pour obtenir des informations relatives aux distributeurs:

Numéro sans frais: 1.800.243.4788

Téléphone: +1.203.393.0010

Pour obtenir de l'information en ligne de distributeurs, visiter LATICRETE à l'adresse suivante [laticrete.com](http://laticrete.com)

### Coût

Communiquez avec le distributeur LATICRETE le plus proche.

## 7. GARANTIE

Voir 10. SYSTÈME DE CLASSIFICATION:

- 1 Year Product Warranty (US - English)
- 5 Year System Warranty (US - English)
- 10 Year System Warranty (US - English)

## 8. ENTRETIEN

LATICRETE and LATAPOXY grouts require routine cleaning with a neutral pH soap and water. All other LATICRETE and LATAPOXY materials require no maintenance but installation performance and durability may depend on properly maintaining products supplied by other manufacturers.

## 9. SERVICES TECHNIQUES

### Soutien technique

Pour tout renseignement, appeler la ligne d'aide du service technique de LATICRETE:

Numéro sans frais: 1.800.243.4788, ext. 1235

Téléphone: +1.203.393.0010, ext. 1235

Télécopieur: +1.203.393.1948

### Documentation technique et de sécurité

Pour obtenir la documentation technique et les consignes de sécurité, visiter notre site Web à [laticrete.com](http://laticrete.com).

## 10. SYSTÈME DE CLASSIFICATION

Des informations supplémentaires sur les produits sont disponibles sur notre site Web à [laticrete.com](http://laticrete.com). Liste des documents connexes:

- DS 230.13: LATICRETE Product Warranty
- DS 231.0: 3701 Mortar Admix
- DS 633.0: LATAPOXY 300 Adhesive
- DS 677.0: 254 Platinum
- DS 34082 : Multimax Lite'
- DS 292 : 257 Titanium

---

LATICRETE International, Inc.

One LATICRETE Park North, Bethany, CT 06524-3423 USA • 1.800.243.4788 • +1.203.393.0010 • [www.laticrete.com](http://www.laticrete.com)

© 2023 LATICRETE International, Inc. All trademarks shown are the intellectual properties of their respective owners.