



L&M™ TRAP ROCK™

DS-175.7E-1224

**Globally Proven
Construction Solutions**



1. NOMBRE DEL PRODUCTO

L&M™ TRAP ROCK™

2. FABRICANTE

LATICRETE International, Inc.

1 LATICRETE Park North

Bethany, CT 06524-3423 USA

Teléfono: +1.203.393.0010, ext. 1235

Línea telefónica gratuita: 1.800.243.4788, ext.

1235

Fax: +1.203.393.1684

Sitio de Internet: laticrete.com

3. DESCRIPCIÓN DEL PRODUCTO

TRAP ROCK is a combination of 100% graded trap rock and portland cement. It is a polyhedral shaped, abrasion resistant, chemically inert, non-absorbent aggregate produced from igneous rock. This dense mineral aggregate is crushed into a polyhedral shape. It is carefully graded to assist ease of placement. This results in interlocking dense mass that produces high performance floors for abrasion resistance. Properly placed, TRAP ROCK reinforces the near wear surface of high traffic floors with one of the densest, most abrasion resistant aggregates on the market today.

033000: Trap Rock Hardened Concrete Floor. Natural Trap Rock Aggregate, pre-mixed with cement, minimum 1.0 lbs/sq.ft. (5 kg/m²). Note to specifier: Up to 1.5 lbs./sq.ft (7 kg/m²) for heavy duty application. "L&M TRAP ROCK" by LATICRETE International, Inc.

Usos

- For heavy duty industrial floors subjected to severe traffic, high abrasion and wear. TRAP ROCK floors are ideal for low maintenance floors in warehouses,

meat processing plants, freezers, floors of grocery chains and distribution centers, heavy industrial and equipment plants, truck, tractor and automotive plants, foundries, and high traffic loading ramps.

Ventajas

- 100% igneous rock aggregate
- High resistance to abrasion
- Heat-resistant
- Densifies floors due to unique polyhedral structure to resist the penetration and attack of oils and other contaminants
- High resistance to friability by distributing single point loads to prevent fracturing, spalling and pitting

Sustratos adecuados

Presentación

Bolsas reforzadas de polietileno multicapas de 25 kg (55 lb).

Rendimiento aproximado

Heavy Duty: 1.0-1.5 lb/ft² (4.9-7.3 kg/m²)

Limitaciones

- Unvented flue and exhaust gasses from heaters and equipment will cause a carbonated floor surface. This results in weak and potentially dusting surfaces. Proper ventilation must be provided.
- Job conditions that influence surface drying and setting times of concrete may affect the timing of the hardener application and finishing procedures.
- Do not add cement, sand, aggregate or admixtures. Follow ACI recommended practices.

Precauciones

- Refer to Safety Data Sheet (SDS) before using
- Protect finished work from traffic until fully cured
- Contains portland cement and silica sand
- May irritate eyes and skin. Avoid contact with eyes or prolonged contact with skin. In case of contact, flush thoroughly with water.
- Do not take internally
- Silica sand may cause cancer or serious lung problems. Avoid breathing dust. Wear a respirator in dusty areas.
- Keep out of reach of children

- Mock-ups and field test areas are required in order to validate performance and appearance related characteristics (including but not limited to color, inherent surface variations, wear, anti-dusting, abrasion resistance, chemical resistance, stain resistance, coefficient of friction, etc.) to ensure system performance as specified for the intended use, and to determine approval of the decorative flooring system.

4. DATOS TÉCNICOS

Las especificaciones están sujetas a cambios sin notificación. Los resultados exhibidos son representativos pero reflejan los procedimientos de prueba utilizados. El desempeño real en el área de trabajo dependerá de los métodos de instalación y de las condiciones del lugar.

5. INSTALACIÓN

• Pre-placement

Air entraining agents, chlorides, admixtures, aggregates, and mixing water that contain chlorides shall not be used in concrete that is to receive TRAP ROCK™. The concrete used in the floor should have a slump of 4-5" and the total air content must not exceed 3%. Stainless steel finishing tools and trowel blades are recommended to insure color integrity.

Method 1 (2/3:1/3 method):

The Standard ACI 302 Method can be used if the TRAP ROCK is to be placed by hand or using a material spreader. Screeding and fill floating (bull floating) shall take place before the emergence of bleed water. After excess bleed water has evaporated or been removed, leaving sufficient moisture at the surface to hydrate cement binders in the TRAP ROCK, evenly distribute approximately 2/3 of the hardener specified for the area. If the hardener sinks into the surface when being applied, the concrete is too plastic for product application.

When the material darkens slightly from absorbed moisture, it should be floated, using hand wooden floats or power floats with float shoes. Do not use combination float and trowel blades. Care should be taken not to tear through the surface of the hardener to the underlying concrete. Do not apply more hardener until moisture from the underlying concrete has been worked completely through the hardener. Immediately apply the remaining 1/3 of the specified amount of hardener at right angles to the first application. The moisture from the underlying concrete must be completely worked through the hardener. If this does not occur, the floor surface may delaminate. Allow to

darken from moisture and float as before. After the concrete has further stiffened, it should be machine or hand troweled to a blemish free finish. If blisters form during the finishing operation they must be immediately ruptured before continuing the finishing operation. The formation of blisters is caused by premature closing of the concrete slab. If blisters occur, the blades of the finishing equipment must be set at a flatter angle with respect to the surface of the concrete slab. Care should be taken not to trowel-burn the surface. Use only stainless steel finishing tools and trowel blades.

Use E-CON™ to prevent rapid evaporation of water from the concrete surface prior to power troweling of the surface. The primary cause of delamination is premature closing of the concrete slab. Premature closing is caused by the float or trowel blades being set at too great an angle with respect to the surface of the concrete slab. This can be prevented by holding the slab open and by delaying the final troweling as long as possible. Keep the angle of the blades of the finishing equipment as flat as possible during all stages of the finishing operation. L&M is not responsible for diluted or mottled color resulting from careless or improper shake application, finishing, curing or failure to protect finished floor from damage by construction trades.

Method 2 (Super flat):

Screed concrete smoothly to avoid excess bull floating. Bull float only once or twice. Excessive floating will close surface, and draw too much water to the surface. This will make the application of TRAP ROCK more difficult. At this time, uniformly apply TRAP ROCK. Apply total lbs./square foot required. Allow moisture from concrete to "wick" into the shake-on material. Begin using a magnesium float on the edges. Once the concrete is walkable and footprints leave no more than 1/8" (3 mm) depression, a trowel machine with float blades can be used to finish the surface. Combination blades are not allowed. Finish concrete to specification. Use E-CON to prevent rapid evaporation of water from the concrete surface prior to power troweling of the surface.

Curing

Apply non-yellowing LUMISEAL WB, protective membrane cure, in strict accordance with the label directions after final troweling and surface water glaze has disappeared. In areas where subsequent treatments, such as SEAL HARD, are scheduled, consult your local L&M representative for specific curing recommendations. Do not wet cure TRAP

ROCK by ponding water for the first 24 hours or by covering with plastic.

- DS 172.9: E-CON™
- DS 174.7: SEAL HARD®
- DS 172.8: LUMISEAL WB

6. DISPONIBILIDAD Y COSTO

Disponibilidad

Los materiales LATICRETE® y LATAPOXY® están disponibles en todo el mundo.

Para obtener información sobre los distribuidores, llame a:

Línea telefónica gratuita: 1.800.243.4788

Teléfono: +1.203.393.0010

Para obtener información sobre los distribuidores en Internet, visite LATICRETE en laticrete.com

Costo

Comuníquese con un distribuidor de LATICRETE de su zona.

7. GARANTÍA

Consulte la Sección 10. SISTEMAS ESPECIALES:

8. MANTENIMIENTO

LATICRETE and LATAPOXY® grouts require routine cleaning with a neutral pH soap and water. All other LATICRETE and LATAPOXY materials require no maintenance but installation performance and durability may depend on properly maintaining products supplied by other manufacturers.

9. DEPARTAMENTO DE ASISTENCIA TÉCNICA

Asistencia técnica

Para obtener más información, comuníquese con la Línea Directa del Departamento de Asistencia Técnica de LATICRETE:

Línea telefónica gratuita:

1.800.243.4788, ext. 1235

Teléfono: +1.203.393.0010, ext. 1235

Fax: +1.203.393.1948

Material informativo sobre aspectos técnicos y de seguridad

Para obtener material sobre aspectos técnicos y de seguridad, visite nuestro sitio web en laticrete.com.

10. SISTEMAS ESPECIALES

Podrá obtener más información sobre los productos en nuestro sitio web laticrete.com. A continuación, encontrará una lista de documentos afines:

- DS 230.13: LATICRETE Product Warranty

LATICRETE International, Inc.

One LATICRETE Park North, Bethany, CT 06524-3423 USA • 1.800.243.4788 • +1.203.393.0010 • www.laticrete.com

© 2024 LATICRETE International, Inc. All trademarks shown are the intellectual properties of their respective owners.