



LATAPOXY® 300 Adhesivo Epóxico

DS-23E-0624

**Globally Proven
Construction Solutions**



1. NOMBRE DEL PRODUCTO

LATAPOXY® 300 Adhesivo Epóxico

2. FABRICANTE

LATICRETE International, Inc.

1 LATICRETE Park North

Bethany, CT 06524-3423 USA

Teléfono: +1.203.393.0010, ext. 1235

Línea telefónica gratuita: 1.800.243.4788, ext.

1235

Fax: +1.203.393.1684

Sitio de Internet: laticrete.com

3. DESCRIPCIÓN DEL PRODUCTO

LATAPOXY BIOGREEN is a high strength, chemical resistant, epoxy adhesive that contains Biobased materials derived from renewable resources. Biobased materials provide an alternative to conventional non-renewable materials such as petroleum derived products, contribute to a cleaner environment and may contribute to LEED V4 points. LATAPOXY BIOGREEN will bond to most sound, clean surfaces, spreads easily and cleans with water while fresh. LATAPOXY BIOGREEN is available in a factory-proportioned kit consisting of epoxy resin, hardener, and chemical resistant silica filler. LATAPOXY BIOGREEN can be used in interior and exterior (see limitations) walls and floors, wet and dry areas.

Usos

- For heavy duty commercial chemical resistant installations in food processing areas, commercial kitchens, restaurants, etc. Also use LATAPOXY

BIOGREEN to install all types of ceramic tile, marble and natural stone over post-tensioned floor systems. Also recommended for rubber flooring and wood block floors, the installation of green marble, white marble, and resin backed tiles and stones agglomerate marbles that have a tendency to stain, darken or warp when installed with water-based installation materials.

- Note: The Tile Council of North America recommends the use of epoxy adhesives and grouts for thin-set installations on suspended concrete slabs and for floors and walls when chemical resistance is required.

Ventajas

- Made with Biobased materials
- Water cleanable
- No flammable solvents are required to clean tools or finished work
- Ideal for installing moisture sensitive marble and agglomerate tiles
- Ideal for the installation of resin backed tile
- Non-staining on white and light-colored marble
- High bond strength
- Ideal for mosaics, stone, and agglomerates
- Maximum chemical resistance
- Conforms to ISO 13007 with an R2 Classification

Sustratos adecuados

Presentación

Unit consists of the following components:

- 2 pouches of Part A total weight 2 lbs (0.9 kg)
- 2 pouches of Part B total weight 4 lbs (1.8 kg)
- 2 bags of Part C Powder total weight 18 lbs (8.2 kg)

Rendimiento aproximado

	#2 Unit
With 1/16" (1.5 mm) v-notch trowel	125-135 ft ² / 11.6-12.5 m ²
With 3/16" (4 mm) v-notch trowel	40-50 ft ² / 3.7-4.6 m ²
With 1/8" x 1/8" (3 x 3 mm) square notch trowel	60-70 ft ² / 5.6-6.5 m ²
With 1/4" x 1/4" (6 x 6 mm)	30-35 ft ² / 2.8-3.3 m ²

square notch trowel	
---------------------	--

Limitaciones

- For veneer installations using this product, consult local building code requirements regarding limitations and installation system specifications.
- Not for use as a grout. Use SPECTRALOCK® PRO Premium Grout†, SPECTRALOCK PRO Grout†, LATAPOXY® SP-100 or SPECTRALOCK 2000 IG.
- Do not install when surface temperature is below 60°F (16°C) or above 90°F (32°C).
- Not for use as a wear surface.
- Adhesives for ceramic tile and stone are not replacements for waterproofing membranes. When a waterproofing membrane is required, use a LATICRETE® Waterproofing Membrane (see Section 10 FILING SYSTEMS).
- Consult LATICRETE Technical Services on limitations for exterior installations.
- Note: Surfaces must be structurally sound, stable and rigid enough to support ceramic/stone tile, thin brick and similar finishes. Substrate deflection under all live, dead and impact loads, including concentrated loads, must not exceed L/360 for thin bed ceramic tile/brick installations or L/480 for thin bed stone installations where L=span length (except where local building codes specify more stringent deflection requirements)

Precauciones

- Consult SDS for safety information.
- During cold weather, protect finished work from traffic until fully cured.
- LATAPOXY® BIOGREEN™ Part A is corrosive until fully cured. Causes severe skin burns and eye damage.
- Wait 14 days after the final grouting period before filling pools, spas and water features with water at 70°F (21°C).
- Allow grout to cure for 10 days with epoxy grout or 14 days with cement grout prior to turning on steam in a steam room.
- Contains silica sand. Silica sand may cause cancer or serious lung problems. Do not breathe dust. Wear a respirator in dusty areas.
- Keep out of reach of children.

4. DATOS TÉCNICOS

Información del producto VOC/LEED

This product has been certified for Low Chemical Emissions (ULCOM/GG UL2818) under the UL GREENGUARD Certification Program for Chemical Emissions for Building Materials, Finishes and Furnishings (UL 2818 Standard) by UL Environment.

Total VOC Content of product in unused form is 18 g/L.

Propiedades físicas

Test	Method	Specification	Results
Quarry Tile Shear Bond Strength	ANSI A118.3-5.5	>1000 psi (6.9 MPa)	1400-1500 psi (9.6-10.3 MPa)
Tensile Strength	ANSI A118.3-5.7	>1000 psi (6.9 MPa)	1300-1400 psi (8.9-9.6 MPa)
Compressive Strength	ANSI A118.3-5.6	>3500 psi (24.1 MPa)	5000-5400 psi (34.4-37.2 MPa)
Thermal Shock Resistance	ANSI A118.3-5.8	>500 psi (3.4 MPa)	1300-1400 psi (8.9-9.6 MPa)
Shrinkage	ANSI A118.3-5.3	<0.25%	0-0.1%
Sag Resistance	ANSI A118.3-5.4	No shape change	pass
Water Cleanability	ANSI A118.3-5.1	>80 minutes	>80 minutes
Shear Adhesion Strength	ISO 13007-2 4.3.4	?2 N/mm ²	7.5-8 N/mm ²
Shear Adhesion Strength after Water Immersion	ISO 13007-2 4.3.5	?2 N/mm ²	7.5-8 N/mm ²
Shear Adhesion After Thermal Shock	ISO 13007-2 4.3.8	?2 N/mm ²	9.0-9.5 N/mm ²
Open Time: Tensile Adhesion Strength	ISO 13007-2 4.1	>0.5 N/mm ² in not less than 20 minutes	3-3.5 N/mm ² in not less than 20 minutes

Classification in Compliance with EN 12004

LATAPOXY® BIOGREEN is an improved reaction resin adhesive classified as R2

Propiedades de trabajo

Pot Life	45 minutes
Time to Grout	8 hours
Time to Light Traffic	8 hours
Time to Heavy Traffic	12 hours
Wet Density	13.2 lb/gal (1.59 g/ml)

CHEMICAL RESISTANCE CHART

LATAPOXY® BIOGREEN

REAGENT TYPE at (70°F [21°C])	LATAPOXY® BIOGREEN 300 Adhesive EXPOSURE LEVEL	
	Intermittent	Constant
Citric Acid 10%	R	R
Sulfuric Acid 10%	R	R
Hydrochloric Acid 10%	R	R
Lactic Acid 5%	R	R
Vinegar	R	R
Acetic Acid 10%	R	R
Nitric Acid 10%	R	R
Sodium Hydroxide 10%	R	R
Sodium Chloride 10%	R	R
Concentrated Detergents	R	R
Ammonium Hydroxide	R	R
Sugars	R	R
Gasoline	NR	NR
Cooking Oils	R	R
Turpentine	R	R
Mineral Spirits	R	R
Toluene	NR	NR
Xylene	NR	NR

R= Recommended NR= Not Recommended
Chemical Resistance determined in accordance with ASTM C267-1982.

NOTES TO SPECIFIER: Use the constant exposure recommendations for intermittent exposure to reagents at temperatures above 90°F (32°C).

Las especificaciones están sujetas a cambios sin notificación. Los resultados exhibidos son representativos pero reflejan los procedimientos de prueba utilizados. El desempeño real en el área de trabajo dependerá de los métodos de instalación y de las condiciones del lugar.

5. INSTALACIÓN

• Surface Preparation

All surfaces should be between 60°F (16°C) and 90°F (32°C) and structurally sound, clean and free of all dirt, oil, grease, paint, concrete sealers or curing compounds. Rough or uneven concrete surfaces should be made smooth with Latex Portland Cement Underlayment to provide a wood float (or better) finish. Installation may be made on a damp surface. New concrete slabs must be damp cured and 28 days old prior to application. All slabs must be plumb and true to within 1/4" (6 mm) in 10 ft (3 m). Expansion joints shall be provided through the tile work from all construction or expansion joints in the substrate. Follow ANSI specification A108.01-3.7 "Requirements for Movement Joints: Preparations by Other Trades" or TCNA detail EJ-171 "Movement Joints—Vertical & Horizontal". Do not cover expansion joints with mortar.

Note: Temperature will effect working properties of LATAPOXY BIOGREEN. Warm temperatures will speed curing and shorten working time. Cool temperatures will slow curing and require longer time to traffic. Store LATAPOXY BIOGREEN at 70°F (21°C) for 24 hours prior to use.

1. Installer must verify that deflection under all live, dead and impact loads of interior plywood floors does not exceed industry standards of L/360 for ceramic tile and brick or L/480 for stone installations where L=span length.
2. Minimum construction for interior plywood floors.
SUBFLOOR: 5/8" (15 mm) thick exterior glue plywood, either plain with all sheet edges blocked or tongue and groove, over bridged joints spaced 16" (400 mm) o.c. maximum; fasten plywood 6" (150 mm) o.c. along sheet ends and 8" (200 mm) o.c. along intermediate supports with 8d ring-shank, coated or hot dip galvanized nails (or screws); allow 1/8" (3 mm) between sheet ends and 1/4" (6 mm) between sheets edges; all sheet ends must be supported

by a framing member; glue sheets to joints with construction adhesive.

UNDERLAYMENT: 5/8" (15 mm) thick exterior glue plywood fastened 6" (150 mm) o.c. along sheet ends and 8" (200 mm) o.c. in the panel field (both directions) with 8d ring-shank, coated or hot dip galvanized nails (or screws); allow 1/8" (3 mm) to 1/4" (6 mm) between sheets and 1/4" (6 mm) between sheet edges and any abutting surfaces; offset underlayment joints from joints in subfloor and stagger joints between sheet ends; glue underlayment to subfloor with construction adhesive. Refer to Technical Data Sheet 152 "Bonding Ceramic Tile Stone or Brick Over Wood Floors" for complete details.

3. DO NOT bond to particle board, OSB, luan, Masonite® or hardwood surfaces.

Mixing

Pour LATAPOXY® BIOGREEN™ Part A and Part B into a clean mixing pail and mix thoroughly for 90 seconds. Add LATAPOXY 300 Part C Filler Powder and mix to a smooth, trowelable consistency. Mortar is ready for use immediately after mixing.

Application

Apply mortar to the substrate with the flat side of the trowel, pressing firmly to work into surface. Comb on additional mortar with the notched side.

Note: Use the proper sized notched trowel to ensure full bedding of the tile. Back butter large tiles > 8" x 8" (>200 mm x 200 mm) to provide full bedding and firm support. Place tiles into wet, sticky mortar and beat in using a beating block and rubber mallet to embed tile and adjust level. Check mortar for complete coverage by periodically removing a tile and inspecting bedding mortar transfer onto back of tile.

6. DISPONIBILIDAD Y COSTO

Disponibilidad

Los materiales LATICRETE® y LATAPOXY® están disponibles en todo el mundo.

Para obtener información sobre los distribuidores, llame a:

Línea telefónica gratuita: 1.800.243.4788

Teléfono: +1.203.393.0010

Para obtener información sobre los distribuidores en Internet, visite LATICRETE en laticrete.com

Costo

Comuníquese con un distribuidor de LATICRETE de su zona.

7. GARANTÍA

Consulte la Sección 10. SISTEMAS ESPECIALES:

- 25 Year System Warranty (US) (English)
- 1 Year Product Warranty (US) (English)
- LATICRETE Lifetime System Warranty (US) (English)

8. MANTENIMIENTO

LATICRETE and LATAPOXY® grouts require routine cleaning with a neutral pH soap and water. All other LATICRETE and LATAPOXY® materials require no maintenance but installation performance and durability may depend on properly maintaining products supplied by other manufacturers.

9. DEPARTAMENTO DE ASISTENCIA TÉCNICA

Asistencia técnica

Para obtener más información, comuníquese con la Línea Directa del Departamento de Asistencia Técnica de LATICRETE:

Línea telefónica gratuita:

1.800.243.4788, ext. 1235

Teléfono: +1.203.393.0010, ext. 1235

Fax: +1.203.393.1948

Material informativo sobre aspectos técnicos y de seguridad

Para obtener material sobre aspectos técnicos y de seguridad, visite nuestro sitio web en laticrete.com.

10. SISTEMAS ESPECIALES

Podrá obtener más información sobre los productos en nuestro sitio web laticrete.com. A continuación, encontrará una lista de documentos afines:

- DS 230.13: LATICRETE Product Warranty
- DS 230.99: LATICRETE Lifetime System Warranty (United States and Canada)
- DS 030.0: SPECTRALOCK® 2000 IG
- DS 236.0: 9235 Waterproofing Membrane
- DS 631.0: LATAPOXY SP-100
- DS 663.0: HYDRO BAN®
- DS 681.0: SPECTRALOCK PRO Premium Grout†
- DS 685.0: SPECTRALOCK PRO Grout†

LATICRETE International, Inc.

One LATICRETE Park North, Bethany, CT 06524-3423 USA • 1.800.243.4788 • +1.203.393.0010 • www.laticrete.com

© 2024 LATICRETE International, Inc. All trademarks shown are the intellectual properties of their respective owners.

- TDS 179: Pool Maintenance Guide