



# Self-Leveling Underlayments Cured Weights by Depth

Product	NXT® Level Flow	NXT Level	NXT Level Plus	NXT Level Plus Lite	SUPERCAP® SC500	SUPERCAP SC500 Plus	SUPERCAP SC500-LW
<b>Density: Pounds per Cubic Foot</b>	<b>125</b>	<b>130</b>	<b>130</b>	<b>70</b>	<b>125</b>	<b>130</b>	<b>87</b>
<b>Depth in Inches (Millimeters)</b>	<b>Pounds per Square Feet</b>						
1/4" (6.4 mm)	2.6 (1.2 kg)	2.7 (1.2 kg)	2.7 (1.2 kg)	1.5 (0.7 kg)	2.6 (1.2 kg)	2.7 (1.2 kg)	1.8 (0.8 kg)
1/2" (12.7 mm)	5.2 (2.4 kg)	5.4 (2.5 kg)	5.4 (2.5 kg)	2.9 (1.3 kg)	5.2 (2.4 kg)	5.4 (2.5 kg)	3.6 (1.6 kg)
3/4" (19.1 mm)	7.8 (3.5 kg)	8.1 (3.7 kg)	8.1 (3.7 kg)	4.4 (2.0 kg)	7.8 (3.5 kg)	8.1 (3.7 kg)	5.4 (2.5 kg)
1" (25.4 mm)	10.4 (4.7 kg)	10.8 (4.9 kg)	10.8 (4.9 kg)	5.8 (2.6 kg)	10.4 (4.7 kg)	10.8 (4.9 kg)	7.3 (3.3 kg)
1-1/4" (31.8 mm)	13.0 (5.9 kg)	13.5 (6.1 kg)	13.5 (6.1 kg)	7.3 (3.3 kg)	13.0 (5.9 kg)	13.5 (6.1 kg)	9.1 (4.1 kg)
1-1/2" (38.1 mm)	15.6 (7.1 kg)	16.3 (7.4 kg)	16.3 (7.4 kg)	8.8 (4.0 kg)	15.6 (7.1 kg)	16.3 (7.4 kg)	10.9 (5.0 kg)
1-3/4" (44.5 mm)	18.2 (8.3 kg)	19.0 (8.6 kg)	19.0 (8.6 kg)	10.2 (4.6 kg)	18.2 (8.3 kg)	19.0 (8.6 kg)	12.7 (5.8 kg)
2" (50.8 mm)	20.8 (9.4 kg)	21.7 (9.8 kg)	21.7 (9.8 kg)	11.7 (5.3 kg)	20.8 (9.4 kg)	21.7 (9.8 kg)	14.5 (6.6 kg)
2-1/4" (57.2 mm)		24.4 (11.1 kg)		13.1 (5.9 kg)	23.4 (10.1 kg)	24.4 (11.1 kg)	16.3 (7.4 kg)
2-1/2" (63.5 mm)		27.1 (12.3 kg)		14.6 (6.6 kg)	26.0 (11.8 kg)	27.1 (12.3 kg)	18.1 (8.2 kg)
2-3/4" (69.9 mm)		29.8 (13.5 kg)		16.0 (7.3 kg)	28.6 (13.0 kg)	29.8 (13.5 kg)	19.9 (9.0 kg)
3" (76.2 mm)		32.4 (14.7 kg)		17.5 (7.9 kg)	31.2 (14.2 kg)	32.4 (14.7 kg)	21.8 (9.9 kg)
3-1/4" (82.6 mm)				19.0 (8.6 kg)			23.6 (10.7 kg)
3-1/2" (88.9 mm)				20.4 (9.3 kg)			25.4 (11.5 kg)
3-3/4" (95.3 mm)				21.9 (9.9 kg)			27.2 (12.3 kg)
4" (101.6 mm)				23.3 (10.6 kg)			29.0 (13.2 kg)

Other Building Products	Density: Pounds per Cubic Foot	Pounds per Square Feet at 1"
Concrete	145	12.1 (5.5 kg)
Gypsum Self Leveling Underlayment	110	9.2 (4.2 kg)
Lightweight Concrete	90 to 100	8.0 (3.6 kg)





# Revestimientos autonivelantes, peso curado por profundidad

Producto	NXT® Level Flow	NXT Level	NXT Level Plus	NXT Level Plus Lite	SUPERCAP® SC500	SUPERCAP SC500 Plus	SUPERCAP SC500-LW
<b>Densidad: Libras por pie cúbico</b>	<b>125</b>	<b>130</b>	<b>130</b>	<b>70</b>	<b>125</b>	<b>130</b>	<b>87</b>
<b>Profundidad en milímetros (pulgadas)</b>	<b>Pounds per Square Feet</b>						
6.4 mm (1/4")	1.2 kg (2.6)	1.2 kg (2.7)	1.2 kg (2.7)	0.7 kg (1.5)	1.2 kg (2.6)	1.2 kg (2.7)	0.8 kg (1.8)
12.7 mm (1/2")	2.4 kg (5.2)	2.5 kg (5.4)	2.5 kg (5.4)	1.3 kg (2.9)	2.4 kg (5.2)	2.5 kg (5.4)	1.6 kg (3.6)
19.1 mm (3/4")	3.5 kg (7.8)	3.7 kg (8.1)	3.7 kg (8.1)	2.0 kg (4.4)	3.5 kg (7.8)	3.7 kg (8.1)	2.5 kg (5.4)
25.4 mm (1")	4.7 kg (10.4)	4.9 kg (10.8)	4.9 kg (10.8)	2.6 kg (5.8)	4.7 kg (10.4)	4.9 kg (10.8)	3.3 kg (7.3)
31.8 mm (1-1/4")	5.9 kg (13.0)	6.1 kg (13.5)	6.1 kg (13.5)	3.3 kg (7.3)	5.9 kg (13.0)	6.1 kg (13.5)	4.1 kg (9.1)
38.1 mm (1-1/2")	7.1 kg (15.6)	7.4 kg (16.3)	7.4 kg (16.3)	4.0 kg (8.8)	7.1 kg (15.6)	7.4 kg (16.3)	5.0 kg (10.9)
44.5 mm (1-3/4")	8.3 kg (18.2)	8.6 kg (19.0)	8.6 kg (19.0)	4.6 kg (10.2)	8.3 kg (18.2)	8.6 kg (19.0)	5.8 kg (12.7)
50.8 mm (2")	9.4 kg (20.8)	9.8 kg (21.7)	9.8 kg (21.7)	5.3 kg (11.7)	9.4 kg (20.8)	9.8 kg (21.7)	6.6 kg (14.5)
57.2 mm (2-1/4")		11.1 kg (24.4)		5.9 kg (13.1)	10.1 kg (23.4)	11.1 kg (24.4)	7.4 kg (16.3)
63.5 mm (2-1/2")		12.3 kg (27.1)		6.6 kg (14.6)	11.8 kg (26.0)	12.3 kg (27.1)	8.2 kg (18.1)
69.9 mm (2-3/4")		13.5 kg (29.8)		7.3 kg (16.0)	13.0 kg (28.6)	13.5 kg (29.8)	9.0 kg (19.9)
76.2 mm (3")		14.7 kg (32.4)		7.9 kg (17.5)	14.2 kg (31.2)	14.7 kg (32.4)	9.9 kg (21.8)
82.6 mm (3-1/4")				8.6 kg (19.0)			10.7 kg (23.6)
88.9 mm (3-1/2")				9.3 kg (20.4)			11.5 kg (25.4)
95.3 mm (3-3/4")				9.9 kg (21.9)			12.3 kg (27.2)
101.6 mm (4")				10.6 kg (23.3)			13.2 kg (29.0)

Otros productos de construcción	Densidad: Libras por pie cúbico	Libras por pie cuadrado a 1"
Concreto	145	5.5 kg (12.1)
Solado autonivelante a base de yeso	110	4.2 kg (9.2)
Concreto liviano	90 to 100	3.6 kg (8.0)

