



1500 Sanded Grout

DS-256-0820

**Globally Proven
Construction Solutions**



1. PRODUCT NAME

1500 Sanded Grout

2. MANUFACTURER

LATICRETE International, Inc.

1 LATICRETE Park North

Bethany, CT 06524-3423 USA

Telephone: +1.203.393.0010, ext. 1235

Toll Free: 1.800.243.4788, ext. 1235

Fax: +1.203.393.1684

Website: laticrete.com

3. PRODUCT DESCRIPTION

1500 Sanded Grout is a premium, factory prepared grout designed to be mixed with water. 1500 Sanded Grout is formulated from a blend of high strength portland cement, graded aggregates, polymers and color-fast pigments and provides a grout joint that is dense, hard and durable.

Uses

- For grout joint widths of 1/16" (1.5 mm) up to 3/8" (9 mm).

Advantages

- Exceeds ANSI A118.6 Specifications.
- Mix with water, or for improved performance fortify with 1776 Grout Enhancer which is equipped with anti-microbial technology.
- Designed for exterior and interior use - ideal for both heavy duty use outdoors and for long lasting beauty indoors.
- Uniform color - Grout colors are specially blended to be uniform in color.
- Available in a range of exciting colors that should satisfy even the most discriminating tastes.

- Part of a complete system that includes materials for every aspect of a tile installation to ensure quality and long lasting performance.

Suitable Substrates

Packaging

All other colors available in Full Batch quantities. See your local LATICRETE Sales Representative for details. 44 Bright White, 90 Light Pewter, 40 Latte, 39 Mushroom, 78 Sterling Silver, 24 Natural Grey, 17 Marble Beige, 88 Silver Shadow, 23 Antique White, 89 Smoke Grey

25 lb (11.3 kg) colors available:

25 lb (11.3 kg) bags; 104 bags per pallet

Approximate Coverage

See Grout Color Chart for coverage information

Shelf Life

Factory sealed containers of this product are guaranteed to be of first quality for two (2) years.

Limitations

- Adhesives/mastics, mortars and grouts for ceramic tile, pavers, brick and stone are not replacements for waterproofing membranes. When a waterproofing membrane is required, use a LATICRETE® Waterproofing Membrane (see Section 10 FILING SYSTEM).
- Not for use with absorbent tile. For absorbent tile and polished marble use 1600 Unsanded Grout.
- DO NOT use for chemical resistance. Use SPECTRALOCK® 2000 IG when chemical resistance is required.
- DO NOT use acid to clean colored grout joints.
- Job site conditions will affect the final color of colored grouts. Try a small test area to determine your results before grouting the entire installation.
- Certain types of tile are more absorbent than others and will trap color pigment during grouting.
- Prior to grouting, test for absorption of color pigment. Porous tiles will need to be sealed prior to grouting.
- Selecting Other Grouting Materials: LATICRETE has grouting materials designed for every use. For installations that require high strength and chemical resistance choose SPECTRALOCK 2000 IG.

- 1500 Sanded Grout is designed to be mixed with either water or 1776 Grout Enhancer. Do not mix other grout additives with this product. Use of other grout additives may result in color variation and reduced product performance and will void all LATICRETE warranties.

Cautions

- Consult SDS for more safety information.
- During cold weather, protect finished work from traffic until fully cured.
- Contains portland cement and silica sand. Wear protective gloves, clothing and eye protection. In case of contact, flush thoroughly with water.
- In submerged applications or steam rooms, allow 1500 Sanded Grout to cure 14 days at 70°F (21°C) before use of area and filling with water. See TDS 192 for more information on these applications.
- DO NOT take internally. Silica sand may cause cancer, respiratory irritation or serious lung problems. Do not breathe dust. Wear a respirator in dusty areas.
- Keep out of reach of children.

4. TECHNICAL DATA

VOC/LEED Product Information

This product has been certified for Low Chemical Emissions (ULCOM/GG UL2818) under the UL GREENGUARD Certification Program for Chemical Emissions for Building Materials, Finishes and Furnishings (UL 2818 Standard) by UL Environment.

Total VOC Content pounds/gallon (grams/liter) of product in unused form is 0.00 lb/gal (0.00 g/?)

Applicable Standard

- ANSI A118.6
- This product has a cradle-to-gate (with options) Product-Specific (Type III) Environmental Product Declaration. The PCR review, life cycle assessment and declaration were independently verified by UL Environment in accordance with ISO 14025, ISO 14040 and ISO 14044.

Physical Properties

1500 Sanded Grout mixed with water (70°F [21°C])

Test/Test Method	Results
Water Absorption ANSI A118.6 4.4	5 – 7%
Compressive Strength ANSI A118.6 4.5	3500–4500 psi (24.1 – 31 MPa)
Linear Shrinkage ANSI A118.6 4.3	<0.2%

Working Properties

1500 Sanded Grout mixed with water (70°F [21°C])

Pot Life	1–2 hours
Foot Traffic	12 hours
Heavy Traffic	24 hours
Wet Density	15.9 lb/gal (1.9 g/ml)

Specifications subject to change without notification. Results shown are typical but reflect test procedures used. Actual field performance will depend on installation methods and site conditions.

5. INSTALLATION

• Surface Preparation

Before starting to grout, remove spacers and debris in grout joints and remove dust and dirt using a wet sponge. Do not leave water standing in joints. Substrate temperature must be between 40°F (4°C) and 90°F (32°C). Apply grout release or sealer if necessary. Refer to TDS 400 "Grout Guide" for more information on grouting.

Mixing

Use approximately 2–2-3/8 quarts (1.9 – 2-1/4 L) of clean potable water for 25 lbs (11.3 kg) of 1500 Sanded Grout powder and/or 1776. Place water in a clean mixing container and add grout powder slowly. Mix by hand or with a slow speed mixer to a smooth stiff consistency. Allow to slake for 5–10 minutes and remix.

Application

Dampen tile surface with water. Spread with a sharp, firm rubber grout float. Work the grout paste into the joints until completely filled. Use diagonal strokes to pack the joints. Ensure that joint is filled and grout is not just sitting on top (i.e. "bridging the joint").

Note: For fuller, flush joints sprinkle a thin layer of dry grout powder over surface immediately after grouting. When grout darkens over joint, buff with burlap, carpet remnant or cotton rag to pack joint and clean face of tile.

Cleaning

Grout Primary Cleaning—Remove excess grout from the face of the tiles with the edge of the grout float. Hold the float at a 90° angle and pull it at a 45° angle diagonally across the joints and tile to avoid pulling out the material.

Grout Secondary Cleaning—Remove remaining grout with a damp sponge (not wet) or a damp towel. Work diagonally to the joints. Allow to dry. When the grout joints are firm,

polish the surface with a coarse nylon pad or coarse cloth and minimal water.

Note: Use caution when polishing soft glazed tiles or polished stone.

Selecting Other Grout Materials

LATICRETE has grouting materials designed for every use. For exceptional stain resistance in most installations choose SPECTRALOCK® PRO Premium Grout†. For installations that require high strength and chemical resistance choose SPECTRALOCK 2000 IG. These products are ideal for installations where a stain resistant, colorfast grout is desired.

6. AVAILABILITY AND COST

Availability

LATICRETE materials are available worldwide.

For Distributor Information, Call:

Toll Free: 1.800.243.4788

Telephone: +1.203.393.0010

For on-line distributor information, visit LATICRETE at laticrete.com

Cost

Contact a LATICRETE Distributor in your area.

7. WARRANTY

See 10. FILING SYSTEM:

- DS 230.13: 1 Year Product Warranty

8. MAINTENANCE

LATICRETE recommends using STONETECH® surface products to protect, clean and enhance stone, masonry, tile and grout surfaces. Protect surfaces from common stains by using a STONETECH sealer such as STONETECH BulletProof® Sealer. Routine maintenance should follow with STONETECH Revitalizer® Cleaner and Protector or a neutral pH cleaner such as STONETECH Stone & Tile Cleaners. For tough or difficult to remove soil use STONETECH KlenzAll™ Cleaner, a nylon scrubbing pad or a long handled stiff bristle brush. For additional information, please refer to the Grout Guide, TDS 400 and TDS 113 Cement Grout Care & Maintenance for more information.

9. TECHNICAL SERVICES

Technical Assistance

Information is available by calling the LATICRETE Technical Service Hotline:

Toll Free: 1.800.243.4788, ext. 1235

Telephone: +1.203.393.0010, ext. 1235

Fax: +1.203.393.1948

Technical and Safety Literature

To acquire technical and safety literature, please visit our website at laticrete.com.

10. FILING SYSTEM

Additional product information is available on our website at laticrete.com. The following is a list of related documents:

- DS 230.13: LATICRETE Product Warranty
- DS 030.0: SPECTRALOCK® 2000 IG
- DS 236.0: 9235 Waterproofing Membrane
- DS 258.0: 1600 Unsanded Grout
- DS 265.0: 1776 Grout Enhancer
- DS 633.0: HYDRO BAN®
- DS 681.0: SPECTRALOCK PRO Premium Grout†
- TDS 192: Installation of Ceramic Tile in Swimming Pools
- TDS 400: Grout Guide

LATICRETE International, Inc.

One LATICRETE Park North, Bethany, CT 06524-3423 USA • 1.800.243.4788 • +1.203.393.0010 • www.laticrete.com

© 2020 LATICRETE International, Inc. All trademarks shown are the intellectual properties of their respective owners.